


Technical information



R

General information	R2~R19
ISO13399 compliant dimension markings	R2
SI unit conversion table / Cutting symbol	R6
Surface roughness	R7
Heat treatment and hardness expression	R8
Vickers hardness conversion chart	R9
Material list (JIS)	R10
Material cross reference table	R11
Various cross reference tables	R20~R29
Insert grades cross reference table	R20
Molded chipbreaker cross reference table	R26
Milling insert description cross reference table	R28
Terms and angles of toolholder	R30~R35
Turning toolholder	R30
Milling cutter	R31
End mills	R32
Solid drills	R33
Precautions when using wiper inserts	R34
Trouble shooting	R38~R41
Cutting edges figuration and countermeasures	R38
Turning	R39
Milling	R40
Drilling	R41
Basic formulas	R42~R45
Turning	R42
Milling	R44
Drilling	R45
Tooling examples of small parts machining	R46~R55
Tooling example	R46
Automatic lathe list by manufacturer	R48
List of instruments and applicable small parts machining and toolholders	R54
Parts compatibility of lever lock toolholders	R55

R1

ISO13399 Compliant dimension markings



All dimension markings in the catalog are complied with ISO13399.
Symbol, detail and previous symbol are shown below.

1. Insert

Symbol	Detail	Previous symbol
AN	Relief angle	α
D1	Hole diameter	ϕd
IC	I.C. Size	A
RE	Corner-R	$r\epsilon$
S	Insert thickness	T

2. Toolholder for external

Symbol	Detail	Previous symbol
B	Shank width	B
H	Shank height	H1
HF	Edge height	h
LF	Overall length	L1
LH	Head length	L2
WF	Functional width	F1






3. Small parts machining

Symbol	Detail	Previous symbol
B	Shank width	B
H	Shank height	H1
HF	Edge height	h
LF	Overall length	L1
LH	Head length	L2
LU	Usable length	L2
WF	Functional width	F1

4. Boring bars

Symbol	Detail	Previous symbol
DMIN	Min. bore dia.	ϕA
DCON	Shank dia.	$\phi D, \phi D1$
GAMO	Rake angle	θ
H	Shank width	H
LF	Overall length	L1
LH	Head length	L2
LPR	Overall length	L1
LU	Usable length	L2
RE	Corner-R	$r\epsilon$
WF	Functional width	F



R



Technical information

R2


ISO13399 Compliant dimension markings

5. Grooving / Cut-off inserts

Symbol	Detail	Previous symbol
IC	I.C. Size	A
BCH	Chamfer width	C
CDX	Max. cutting depth	B
CW	Edge width	W
D1	Hole diameter	ϕd
DAXN	External dia. of the groove (max.)	ϕD
DAXX	External dia. of the groove (min.)	ϕD
INSL	Insert length	L
PSIR%L	Lead angle	θ
RE	Corner-R	$r \epsilon$
S	Insert thickness	H, T
W1	Insert width	A

6. Grooving / Cut-off toolholders

Symbol	Detail	Previous symbol
B	Shank width	B
CDX	Max. cutting depth	T
CUTDIA	Max. cut-off dia.	ϕD_{max}
DAXN	External dia. of the groove (max.)	ϕD
DAXX	External dia. of the groove (min.)	ϕD
DCB	Connection bore dia. (Sleeve)	ϕd_1
DMIN	Min. Bore dia.	ϕA
DCON	Shank dia.	$\phi D, \phi d_1$
H	Shank height	H1
HF	Edge height	h
LF	Overall length	L1
LH	Head length	L2
WF	Functional width	F1



R



Technical information

R3

ISO13399 Compliant dimension markings

7. Threading inserts

Symbol	Detail	Previous symbol
IC	I.C. Size	A
D1	Hole diameter	ϕd
PNA	Thread angle	θ
PDX	Profile distance	S
S	Insert thickness	T
RE	Corner-R	rε

8. Threading toolholders


Symbol	Detail	Previous symbol
B	Shank width	B
DMIN	Min. Bore dia.	ϕA
DCON	Shank dia.	ϕD
H	Shank height	H1
HF	Edge height	h
LF	Overall length	L1
LH	Head length	L2
LU	Usable length	L2
WF	Functional width	F, F1

9. Inserts for drill

Symbol	Detail	Previous symbol
IC	I.C. Size	A
D1	Hole diameter	ϕd
DC	Drill dia.	ϕD_c
PL	Insert point length	Lp
RE	Corner-R	rε
S	Insert thickness	T
INSL	Insert length	A
W1	Insert width	W

10. Drill holder

Symbol	Detail	Previous symbol
DC	Drill dia.	ϕD_c
DCON	Shank dia.	ϕD_s
OAL	Overall length	L
LU	Usable length (Drilling depth)	L3
PL	Insert point length	Lp
LS	Shank length	Ls
DCSFM5	Flange dia.	ϕd_1
LFS	Functional length	L1
LCF	Flute length	L2



Technical information



R4





ISO13399 Compliant dimension markings

11. Solid end mill

Symbol	Detail	Previous symbol
APMX	Max. depth of cut	ℓ
CHW	Chamfer width	C
DC	Cutting dia.	ϕD_c
DCON	Shank dia.	ϕD_s
DN	Neck dia.	ϕD_1
LF	Overall length	L
LU	Under neck length	ℓ_2
RE	Corner-R	r_e, r
ZEFP	No. of inserts	Z

12. Solid drill

Symbol	Detail	Previous symbol
OAL	Overall length	L
DC	Cutting dia.	ϕD_c
DCON	Shank dia.	ϕD_s
LCF	Flute length	ℓ
LN	Under neck length	ℓ_2
LS	Shank length	l_s
LU	Usable length	ℓ_e






13. Milling inserts

Symbol	Detail	Previous symbol
BCH	Corner chamfer length	X
BS	Wiper edge width	Z
D1	Hole diameter	ϕd
IC	I.C. Size	A
INSL	Insert length	W
L	Cutting edge length	W
RE	Corner-R	r_e
S	Insert thickness	T

14. Toolholder for milling

Symbol	Detail	Previous symbol
APMX	Max. depth of cut	S
CBDP	Connection bore depth	E
DC	Cutting dia.	ϕD
DCB	Bore dia.	ϕd
DCON	Shank dia.	ϕD_s
DCSFSMS	Contact surface dia.	ϕD_2
DCX	Maximum cutting dia.	ϕD_1
KDP	Keyway depth	a
KWW	Keyway width	b
LF	Toolholder height	H
LH	Head length	ℓ



R



Technical information

R5

SI unit conversion table / Cutting symbol

SI derived units conversion chart

Bold units are the ones by SI derived unit.

Extracted from JIS handbook "Iron & steel"

Force

N	kgf	dyn
1	$1.019\ 72 \times 10^{-1}$	1×10^5
9.806 65	1	$9.806\ 65 \times 10^5$
1×10^5	$1.019\ 72 \times 10^{-6}$	1

Stress

Pa or N/m ²	MPa or N/mm ²	kgf/mm ²	kgf/cm ²	kgf/m ²
1	1×10^{-6}	$1.019\ 72 \times 10^{-7}$	$1.019\ 72 \times 10^{-5}$	$1.019\ 72 \times 10^{-1}$
1×10^6	1	$1.019\ 72 \times 10^{-1}$	$1.019\ 72 \times 10$	$1.019\ 72 \times 10^5$
$9.806\ 65 \times 10^6$	9.806 65	1	1×10^2	1×10^6
$9.806\ 65 \times 10^4$	$9.806\ 65 \times 10^{-2}$	1×10^{-2}	1	1×10^4
9.806 65	$9.806\ 65 \times 10^{-6}$	1×10^{-6}	1×10^{-4}	1

Pressure

Pa	kPa	MPa	bar	kgf/cm ²
1	1×10^{-3}	1×10^{-6}	1×10^{-5}	$1.019\ 72 \times 10^{-5}$
1×10^3	1	1×10^{-3}	1×10^{-2}	$1.019\ 72 \times 10^{-2}$
1×10^6	1×10^{-3}	1	1×10	$1.019\ 72 \times 10$
1×10^5	1×10^{-2}	1×10^{-1}	1	$1.019\ 72$
$9.806\ 65 \times 10^4$	$9.806\ 65 \times 10$	$9.806\ 65 \times 10^{-2}$	$9.806\ 65 \times 10^{-1}$	1

Cutting symbol

Cutting conditions below are indicated by the new symbols listed in 2nd column.

1. Turning

Cutting conditions	Symbol	Previous symbol	Unit
Cutting speed	V _c	V	m/min
Feed rate	f	f	mm/rev
Depth of cut	a _p	d	mm
Edge width	CW	W	mm
Workpiece dia.	D _m	D	mm
Required power	P _c	P _{kw}	kW
Specific cutting force	k _c	K _s	MPa
Theoretical surface roughness	h	R _z	μm
Corner radius	R _E	R	mm
Revolution	n	N	min ⁻¹

3. Drilling

Cutting conditions	Symbol	Previous symbol	Unit
Cutting speed	V _c	V	m/min
Feed speed	V _f	F	mm/min
Feed rate	f	f	mm/rev
Drill dia.	D _C	D (D _s)	mm
Required power	P _c	P _{kw}	kW
Specific cutting force	k _c	K _s	MPa
Drilling depth	H	d	mm
Revolution	n	N	min ⁻¹

2. Milling

Cutting conditions	Symbol	Previous symbol	Unit
Cutting speed	V _c	V	m/min
Feed speed	V _f	F	mm/min
Feed per tooth	f _z	f	mm/t
Feed rate	f	f	mm/rev
No. of inserts	Z	Z	teeth
Depth of cut	a _p	d	mm
Width of cut	a _e	w	mm
Pick feed	P _f	P _f	mm
Required power	P _c	P _{kw}	kW
Specific cutting force	k _c	K _s	MPa
Chip removal volume	Q	Q	cm ³ /min
Revolution	n	N	min ⁻¹



Technical information

Surface roughness (JIS B 0601-2001)

Theoretical (Geometrical) surface roughness


Theoretical surface roughness for turning indicates the minimum roughness value from the cutting conditions and it is shown by the formula as follows.

$$Rz(h) = \frac{f^2}{8RE} \times 10^3$$

Rz(h): Theoretical surface roughness [μm]

f: Feed rate [mm/rev]

RE: Corner radius of insert [mm]



How to obtain surface roughness values

Type	Symbol	How to obtain	Explanation
Max. height roughness	Rz	Rz is a mean value in micron meter obtained from the distance of the highest peaks and the lowest valleys within the range of sampled reference length (" ℓ ") in the direction of the center line of the roughness curve. Note) When calculating Rz, extraordinarily high or low threads are considered as damages and excluded from the calculation, and only standard lengths are used. $Rz = Rp + Rv$	
Ten points mean roughness	RzJIS	RzJIS is a mean value in micron meter obtained from the distance of 5 highest peaks (Y_p) and the 5 lowest valleys (Y_v) measured from the center line of the roughness curve within the range of sampled reference length " ℓ ". $Rz_{JIS} = \frac{(Y_{p1}+Y_{p2}+Y_{p3}+Y_{p4}+Y_{p5}) + (Y_{v1}+Y_{v2}+Y_{v3}+Y_{v4}+Y_{v5})}{10}$	 $Y_{p1}, Y_{p2}, Y_{p3}, Y_{p4}, Y_{p5}:$ Distance from the mean line to the highest 5 peaks in the range of sampled reference length " ℓ " $Y_{v1}, Y_{v2}, Y_{v3}, Y_{v4}, Y_{v5}:$ Distance from the mean line to the lowest 5 valleys in the range of sampled reference length " ℓ "
Arithmetical mean roughness	Ra	Ra is obtained from the following formula in micron meter, the roughness curve is expressed by $y=f(x)$, the X-axis is in the direction of the center line and the Y-axis is the vertical magnification of the roughness curve in the range of sampled reference length " ℓ ". $Ra = \frac{1}{\ell} \int_0^\ell \{f(x)\} dx$	

Relationship with triangle symbol

Arithmetical mean roughness Ra(μm)	Max. height roughness Rz(μm)	Ten points mean roughness RzJIS(μm)	*(Triangle symbol)
0.025	0.1	0.1	
0.05	0.2	0.2	▽▽▽▽
0.1	0.4	0.4	
0.2	0.8	0.8	
0.4	1.6	1.6	
0.8	3.2	3.2	▽▽▽
1.6	6.3	6.3	
3.2	12.5	12.5	▽▽
6.3	25	25	
12.5	50	50	
25	100	100	▽

* Triangle symbol was removed from JIS standard in the 1994 Revision.

How to Indicate

- When Ra is $1.6\mu\text{m} \rightarrow 1.6\mu\text{mRa}$
- When Rz is $6.3\mu\text{m} \rightarrow 6.3\mu\text{mRz}$
- When RzJIS is $6.3\mu\text{m} \rightarrow 6.3\mu\text{mRzJIS}$

Indication in JIS standard

Example of Ra indication	Example of Rz indication
1. When indicating the upper limit only (when upper limit is $6.3\mu\text{mRa}$) 	1. When indicating the upper limit only indicate surface roughness following the parameter symbol.
2. When indicating both lower and upper limit (when upper limit is $6.3\mu\text{mRa}$, lower limit is $1.6\mu\text{mRa}$) 	2. When indicating both lower and upper limit indicate surface roughness as (upper limit ~ lower limit) following the parameter symbol.

Note: The indications of Ra and Rz are different.

Caution-symbols for surface roughness

The above information is based on JIS B 0601-2001.

However, some symbols were revised as shown in the right table in accordance with ISO Standard from JIS B 0601-2001 version.

Ten Points Mean Roughness (Rz) was eliminated from 2001 version but it still remains as RzJIS reference, since it was popular in Japan.

Type	Symbol of JIS B 0601-1994	Symbol of JIS B 0601-2001
Max. height roughness	Ry	→ Rz
Ten points mean roughness	Rz	→ (RzJIS)
Arithmetical mean roughness	Ra	→ Ra

R




Technical information


R7

Heat treatment and hardness expression

Heat treatment

One of the ways to determine the hardness of steel is the heat treatment and it is classified to 3 types.



Heat treatment method	Detail	Effect
	<ul style="list-style-type: none">· Quenching (Tempering) After heating to 727°C or over, cool rapidly down to 550°C in water or oil.· Normalizing After heating to 727°C or over, cool down rapidly to 600°C and then to normal temperature.· Annealing After heating to 727°C or over, cool down very slowly to 600°C, then to normal temperature.	<p>Quenching makes steel hard. Because it cools down red-hot steel very rapidly in water or oil, but it may promote internal stress. In order to remove such internal stress, tempering is used. (After cooled down once, reheat it to 200°C ~ 600°C)</p> <p>It miniaturizes the crystals. (Steel is also composed of small cells.) It is used to improve the mechanical character or machinability.</p> <p>It miniaturizes the crystals like the process of normalizing, but the crystal size is bigger than that of normalizing. It targets machinability improvement and distortion correction.</p>

Hardness expression

Hardness	Reference standard	Example	Explanation of example
Brinell hardness	JIS Z 2243: 1992	250HB	Hardness value: 250, Hardness symbol: HB
		200 ~ 250HB	When the hardness has the range
Vickers hardness	JIS Z 2244: 1998	640HV	Hardness value: 640, Hardness symbol: HV
Rockwell hardness	JIS Z 2245: 1992	60HRC	Hardness value: 60, Hardness symbol: HRC
Shore hardness	JIS Z 2246: 1992	50HS	Hardness value: 50, Hardness symbol: HS

R



Technical information

R8

Vickers hardness conversion chart

Vickers hardness (HV)	Brinell hardness 10mm dia. ball Load: 3,000kgf (HB)		Rockwell hardness ²⁾			Shore hardness (HS)	Tensile strength MPa ¹⁾	Vickers hardness (HV)	Brinell hardness 10mm dia. ball Load: 3,000kgf (HB)		Rockwell hardness ²⁾			Shore hardness (HS)	Tensile strength MPa ¹⁾
	Standard ball	Tungsten carbide ball	A scale Load: 60kgf Diamond point (HRA)	B scale Load: 100kgf 1.6mm (1/16in) dia. ball (HRB)	C scale Load: 150kgf Diamond point (HRC)				Standard ball	Tungsten carbide ball	A scale Load: 60kgf Diamond point (HRA)	B scale Load: 100kgf 1.6mm (1/16in) dia. ball (HRB)	C scale Load: 150kgf Diamond point (HRC)		
940	-	-	85.6	-	68.0	97		320	303	303	66.4	(107.0)	32.2	45	1005
920	-	-	85.3	-	67.5	96		310	294	294	65.8	-	31.0	-	980
900	-	-	85.0	-	67.0	95		300	284	284	65.2	(105.5)	29.8	42	950
880	-	(767)	84.7	-	66.4	93		295	280	280	64.8	-	29.2	-	935
860	-	(757)	84.4	-	65.9	92		290	275	275	64.5	(104.5)	28.5	41	915
840	-	(745)	84.1	-	65.3	91		285	270	270	64.2	-	27.8	-	905
820	-	(733)	83.8	-	64.7	90		280	265	265	63.8	(103.5)	27.1	40	890
800	-	(722)	83.4	-	64.0	88		275	261	261	63.5	-	26.4	-	875
780	-	(710)	83.0	-	63.3	87		270	256	256	63.1	(102.0)	25.6	38	855
760	-	(698)	82.6	-	62.5	86		265	252	252	62.7	-	24.8	-	840
740	-	(684)	82.2	-	61.8	84		260	247	247	62.4	(101.0)	24.0	37	825
720	-	(670)	81.8	-	61.0	83		255	243	243	62.0	-	23.1	-	805
700	-	(656)	81.3	-	60.1	81		250	238	238	61.6	99.5	22.2	36	795
690	-	(647)	81.1	-	59.7	-		245	233	233	61.2	-	21.3	-	780
680	-	(638)	80.8	-	59.2	80		240	228	228	60.7	98.1	20.3	34	765
670	-	630	80.6	-	58.8	-		230	219	219	-	96.7	(18.0)	33	730
660	-	620	80.3	-	58.3	79		220	209	209	-	95.0	(15.7)	32	695
650	-	611	80.0	-	57.8	-		210	200	200	-	93.4	(13.4)	30	670
640	-	601	79.8	-	57.3	77		200	190	190	-	91.5	(11.0)	29	635
630	-	591	79.5	-	56.8	-		190	181	181	-	89.5	(8.5)	28	605
620	-	582	79.2	-	56.3	75		180	171	171	-	87.1	(6.0)	26	580
610	-	573	78.9	-	55.7	-		170	162	162	-	85.0	(3.0)	25	545
600	-	564	78.6	-	55.2	74		160	152	152	-	81.7	(0.0)	24	515
590	-	554	78.4	-	54.7	-	2055	150	143	143	-	78.7	-	22	490
580	-	545	78.0	-	54.1	72	2020	140	133	133	-	75.0	-	21	455
570	-	535	77.8	-	53.6	-	1985	130	124	124	-	71.2	-	20	425
560	-	525	77.4	-	53.0	71	1950	120	114	114	-	66.7	-	-	390
550	505	517	77.0	-	52.3	-	1905	110	105	105	-	62.3	-	-	-
540	496	507	76.7	-	51.7	69	1860	100	95	95	-	56.2	-	-	-
530	488	497	76.4	-	51.1	-	1825	95	90	90	-	52.0	-	-	-
520	480	488	76.1	-	50.5	67	1795	90	86	86	-	48.0	-	-	-
510	473	479	75.7	-	49.8	-	1750	85	81	81	-	41.0	-	-	-
500	465	471	75.3	-	49.1	66	1705								
490	456	460	74.9	-	48.4	-	1660								
480	448	452	74.5	-	47.7	64	1620								
470	441	442	74.1	-	46.9	-	1570								
460	433	433	73.6	-	46.1	62	1530								
450	425	425	73.3	-	45.3	-	1495								
440	415	415	72.8	-	44.5	59	1460								
430	405	405	72.3	-	43.6	-	1410								
420	397	397	71.8	-	42.7	57	1370								
410	388	388	71.4	-	41.8	-	1330								
400	379	379	70.8	-	40.8	55	1290								
390	369	369	70.3	-	39.8	-	1240								
380	360	360	69.8	(110.0)	38.8	52	1205								
370	350	350	69.2	-	37.7	-	1170								
360	341	341	68.7	(109.0)	36.6	50	1130								
350	331	331	68.1	-	35.5	-	1095								
340	322	322	67.6	(108.0)	34.4	47	1070								
330	313	313	67.0	-	33.3	-	1035								

Extracted from JIS handbook "Iron & steel" (SAE J 417)

Note:

1. 1 MPa = 1 N/mm²

2. Value in () is not in practical use, but reference only.



Technical information

R9

Material list (JIS)

Ferrous materials

Classification	Name of JIS standard	Symbol
Structural steel	Rolled steel for welded structure	SM
	Re-rolled steel	SRB
	Rolled steel for general structure	SS
	Light gauge steel for general structure	SSC
	Hot-rolled steel plate, sheet and strip for automobile structural use	SAPH
Steel sheet	Cold-rolled steel plate, sheet and strip	SPC
	Hot-rolled soft steel plate, sheet and strip	SPH
Steel pipe	Carbon steel pipe for ordinary piping	SGP
	Carbon steel pipe for boiler / heat exchanger	STB
	Seamless steel pipe for high pressure gas cylinder	STH
	Carbon steel pipe for general structural use	STK
	Carbon steel pipe for machine structural use	STKM
	Alloy steel pipe for structural use	STKS
	Stainless steel pipe for machine structural use	SUS-TK
	Steel square pipe for general structural use	STKR
	Alloy steel pipe for ordinary piping	STPA
	Carbon steel pipe for pressure service	STPG
	Carbon steel pipe for high-temperature service	STPT
	Carbon steel pipe for high-pressure service	STS
Machine structural steel	Stainless steel pipe for ordinary piping	SUS-TP
	Carbon steel for machine structural use	SxxC,SxxCK
	Aluminum chromium molybdenum steel	SACM
	Chromium molybdenum steel	SCM
	Chromium steel	SCr
	Nickel chromium steel	SNC
	Nickel chromium molybdenum steel	SNCM
Special steel	Manganese steel and manganese chromium steel for machine structural use	SMn,SMnC
	Carbon tool steel	SK
	Hollow drill steel	SKC
	Alloy tool steel	SKS,SKD,SKT
	High speed tool steel	SKH
	Free cutting carbon steel	SUM
	High carbon chromium bearing steel	SUJ
	Spring steel	SUP
	Stainless steel bar	SUS-B
	Hot-rolled stainless steel plate, sheet and strip	SUS-HP,SUS-HS
Heat-resistant steel	Cold-rolled stainless steel plate, sheet and strip	SUS-CP,SUS-CS
	Heat-resisting steel bar	SUH-B,SUH-CB
	Heat-resisting steel plate and sheet	SUH-HP,SUH-CP
	Corrosion-resisting and heat-resisting superalloy bar	NCF-B
Superalloy	Corrosion-resisting and heat-resisting superalloy plate and sheet	NCF-P

Classification	Name of JIS standard	Symbol
Forged steel	Carbon steel forging	SF
	Chromium molybdenum steel forging	SFCM
	Nickel chromium molybdenum steel forging	SFNCM
Cast iron	Gray cast iron	FC
	Spheroidal graphite cast iron	FCD
	Blackheart malleable cast iron	FCMB
	Whiteheart malleable cast iron	FCMW
	Pearlitic malleable cast iron	FCMP
Cast steel	Carbon cast steel	SC
	High tensile strength carbon cast steel & low alloy cast steel	SCC
	Stainless cast steel	SCS
	Heat-resisting cast steel	SCH
	High manganese cast steel	SCMnH
	Cast steel for high temperature and high pressure service	SCPH

Non-ferrous metals

Classification	Name of JIS standard	Symbol
Copper	Copper and copper alloy sheet / strip	CxxxxP CxxxxPP CxxxxR
	Copper and copper alloy rod and bar	CxxxxBD CxxxxBDS CxxxxBE
Aluminum alloys and aluminum alloys expanded material	Aluminum and Al. alloy sheet / strip	AxxxxP AxxxxPC
	Aluminum and Al. alloy rod, bar, and wire	AxxxxBE AxxxxBES AxxxxBD AxxxxBDS AxxxxW AxxxxWS
Magnesium alloy expanded material	Aluminum and Al. alloy extruded shape	AxxxxS
	Aluminum and Al. alloy forging	AxxxxFD AxxxxFH
Nickel alloy	Magnesium alloy sheet and plate	MP
	Magnesium alloy rod and bar	MB
Titanium expanded material	Nickel copper alloy sheet and plate	NCuP
	Nickel copper alloy rod and bar	NCuB
Casting	Titanium rod and bar	TB
	Brass casting	CAC20x
	High strength brass casting	CAC30x
	Bronze casting	CAC40x
	Phosphoric bronze casting	CAC50x
	Aluminum bronze casting	CAC70x
	Aluminum alloy casting	AC
	Magnesium alloy casting	MC
	Zinc alloy die casting	ZDCx
	Aluminum alloy die casting	ADC
	Magnesium alloy die casting	MD
	White metal	WJ



Material cross reference table

Steel

Classification	Japan	China	USA	UK	Germany	France	Russia
	JIS	GB	AISI/SAE	BS	DIN	NF	ГОСТ
Carbon steel for machine structural use	S10C	08 10	1010	040A10 045A10 045M10	C10E C10R	XC10	
	S12C		1012	040A12		XC12	
	S15C	15	1015	055M15	C15E C15R		
	S17C		1017			XC18	
	S20C	20	1020	070M20 C22 C22E C22R	C22 C22E C22R	C22 C22E C22R	
	S22C		1023				
	S25C	25	1025	C25 C25E C22R	C25 C25E C25R	C25 C25E C25R	
	S28C		1029				25Г
	S30C	30	1030	080A30 080M30 C30 C30E C30R	C30 C30E C30R	C30 C30E C30R	30Г
	S33C						30Г
	S35C	35	1035	C35 C35E C35R	C35 C35E C35R	C35 C35E C35R	35Г
	S38C		1038				35Г
	S40C	40	1039 1040	080M40 C40 C40E C40R	C40 C40E C40R	C40 C40E C40R	40Г
	S43C		1042 1043	080A42			40Г
	S45C	45	1045 1046	C45 C45E C45R	C45 C45E C45R	C45 C45E C45R	45Г
	S48C			080A47			45Г
	S50C	50	1049	080M50 C50 C50E C50R	C50 C50E C50R	C50 C50E C50R	50Г
	S53C		1050 1053				50Г
	S55C	55	1055	070M55 C55 C55E C55R	C55 C55E C55R	C55 C55E C55R	
	S58C	60	1059 1060	C60 C60E C60R	C60 C60E C60R	C60 C60E C60R	60Г
	S09CK			045A10 045M10	C10E	XC10	
	S15CK	15F			C15E	XC12	
	S20CK					XC18	

R



Technical information

R11

Material cross reference table

Steel

Classification	Japan	China	USA	UK	Germany	France	Russia
	JIS	GB	AISI/SAE	BS	DIN	NF	ГОСТ
Nickel chromium steel	SNC236				36NiCr6		40XH
	SNC415	12CrNi2			14NiCr10		
	SNC631	30CrNi3			36NiCr10		30XH3A
	SNC815	12Cr2Ni4		655M13	15NiCr13		
	SNC836	37CrNi3			31NiCr14		
Nickel chromium molybdenum steel	SNCM220	20CrNiMo	8615	805A20			
			8617	805M20	20NiCrMo2	20NCD 2	
			8620	805A22	20NiCrMo2		
			8622	805M22			
	SNCM240		8637		40NiCrMo2-2		
	SNCM415		8640				
	SNCM420	18CrNiMnMoA	4320		17NiCrMo6-4		20XH2M (20XHM)
	SNCM431				30CrNiMo8		
	SNCM439	40CrNiMoA	4340		40NiCrMo6		
	SNCM447				34CrNiMo6		
	SNCM616						
	SNCM625						
	SNCM630						
	SNCM815						
Chromium steel	SCr415	15Cr 15CrA			17Cr3		15X
	SCr420	20Cr	5120		17CrS3		15XA
	SCr430	30Cr	5130 5132	34Cr4 34CrS4	34Cr4 34CrS4	34Cr4 34CrS4	20X
	SCr435	35Cr	5132	37Cr4 37CrS4	37Cr4 37CrS4	37Cr4 37CrS4	30X
	SCr440	40Cr	5140	530M40 41Cr4 41CrS4	41Cr4 41CrS4	41Cr4 41CrS4	35X
	SCr445	45Cr 50Cr					40X
Chromium molybdenum steel	SCM415	15CrMo			15CrMo4		
	SCM418	20CrMo			18CrMo4 18CrMoS4		20XM
	SCM420			708M20	20CrMo5		20XM
	SCM421						
	SCM430	30CrMo 30CrMoA	4130				30XM 30XMA
	SCM432						
	SCM435	35CrMo	4137	34CrMo4 34CrMoS4	34CrMo4 34CrMoS4	34CrMo4 34CrMoS4	35XM
	SCM440	42CrMo	4140 4142	708M40 709M40 42CrMo4 42CrMoS4	42CrMo4 42CrMoS4	42CrMo4 42CrMoS4	
	SCM445		4145 4147				
	SCM822						

Technical information



R12

Material cross reference table

Steel

Classification	Japan	China	USA	UK	Germany	France	Russia
	JIS	GB	AISI/SAE	BS	DIN	NF	ГОСТ
Manganese steel	SMn420	20Mn2	1522	150M19	20Mn5		
	SMn433	30Mn2 35Mn2	1536	150M36	34Mn5		30Г2 35Г2
	SMn438	40Mn2	1541	150M36	36Mn5		35Г2 40Г2
	SMn443	45Mn2	1541				40Г2 45Г2
	SMnC420	15CrMn	5115		16MnCr5		
	SMnC443	40CrMn	5140				
Structural steel with specified hardenability band	SMn420H		1522H				
	SMn433H						
	SMn438H		1541H				
	SMn443H		1541H				
	SMnC420H						
	SMnC443H						
	SCr415H	15CrH			17Cr3 17CrS3		15X
	SCr420H	20Cr1H	5120H		17Cr3		20X
	SCr430H		5130H 5132H	34Cr4 34CrS4	34Cr4 34CrS3	34Cr4 34CrS4	30X
	SCr435H		5135H	37Cr4 37CrS4	37Cr4 34CrS4	37Cr4 37CrS4	35X
	SCr440H	40CrH	5140H	41Cr4 41CrS4	41Cr4 41CrS4	41Cr4 41CrS4	40X
	SCM415H	15CrMoH	4118H		15CrMo5		
	SCM418H				18CrMo4 18CrMoS4		
	SCM420H	20CrMoH	4118H	708H20	18CrMo4		
	SCM435H		4135H 4137H	34CrMo4 34CrMoS4	34CrMo4 34CrMoS4	34CrMo4 34CrMoS4	
	SCM440H	42CrMoH	4140H 4142H	42CrMo4 42CrMoS4	42CrMo4 42CrMoS4	42CrMo4 42CrMoS4	
	SCM445H		4145H 4147H				
	SCM822H						
	SNC415H						
	SNC631H						
	SNC815H	12Cr2Ni4H		655H13	15NiCr13		
	SNCM220H	20CrNiMoH	8617H 8620H 8622H	805H17 805H20 805H22	21NiCrMo2	20N CD 2	
	SNCM420H	20CrNi2MoH	4320H		20NiCrMoS6-4		

R



Technical information

R13

Material cross reference table

Steel

Classification	Japan	China	USA		UK	Germany	France	Russia
	JIS	GB	UNS	AISI	BS	DIN	NF	ГОСТ
Stainless steel	SUS 201	1Cr17Mn6Ni5N	S20100	201			Z12CMN17-07Az	
	SUS 202	1Cr18Mn8Ni5N	S20200	202	284S16			12X17Г9AH4
	SUS 301	1Cr18Mn10Ni5Mo3N 1Cr17Ni7	S30100	301	301S21	X12CrNi17 7	Z11CN17-08	07X16H6
	SUS 301L		S30153			X2CrNiN18-7		
	SUS 301J1					X12CrNi17 7		
	SUS 302	1Cr18Ni9	S30200	302	302S25		Z12CN18-09	12X18H9
	SUS 302B		S30215	302B				
	SUS 303	Y1Cr18Ni9	S30300	303	303S21	X10CrNiS18 9	Z8CNF18-09	
	SUS 303Se	Y1Cr18Ni9Se	S30323	303Se	303S41			12X18H10E
	SUS 304	0Cr18Ni9	S30400	304	304S31	X5CrNi18 10	Z7CN18-09	08X18H10
	SUS 304L	00Cr18Ni10	S30403	304L	304S11	X2CrNi19 11	Z3CN19-11	03X18H11
	SUS 304N1	0Cr18Ni9N	S30451	304N			Z6CN19-09Az	
	SUS 304N2	0Cr19Ni10NbN	S30452					
	SUS 304LN	00Cr18Ni10N	S30453	304LN		X2CrNiN18 10	Z3CN18-10Az	
	SUS 304J1							
	SUS 304J2							
	SUS 304J3		S30431	S30431				
	SUS 305	1Cr18Ni12	S30500	305	305S19	X5CrNi18 12	Z8CN18-12	06X18H11
	SUS 305J1							
	SUS 309S	0Cr23Ni13	S30908	309S			Z10CN24-13	
	SUS 310S	0Cr25Ni20	S31008	310S	310S31		Z8CN25-20	10X23H18
	SUS 316	0Cr17Ni12Mo2	S31600	316	316S31	X5CrNiMo17 12 2	Z7CND17-12-02	
	SUS 316F					X5CrNiMo17 13 3	Z6CND18-12-03	
	SUS 316L	00Cr17Ni14Mo2	S31603	316L	316S11	X2CrNiMo17 13 2	Z3CND17-12-02	
						X2CrNiMo17 14 3	Z3CND17-13-03	03X17H14M3
	SUS 316N	0Cr17Ni12Mo2N	S31651	316N				
	SUS 316LN	00Cr17Ni13Mo2N	S31653	316LN		X2CrNiMoN17 12 2	Z3CND17-11Az	
						X2CrNiMoN17 13 3	Z3CND17-12Az	
	SUS 316Ti		S31635			X6CrNiMoTi17 12 2	Z6CNDT17-12	08X17H13M2T
	SUS 316J1	0Cr18Ni12Mo2Cu2						
	SUS 316J1L	00Cr18Ni14Mo2Cu2						
	SUS 317	0Cr19Ni13Mo3	S31700	317	317S16			
	SUS 317L	00Cr19Ni13Mo3	S31703	317L	317S12	X2CrNiMo18 16 4	Z3CND19-15-04	
	SUS 317LN		S31753				Z3CND19-14Az	
	SUS 317J1	0Cr18Ni16Mo5						
	SUS 317J2							
	SUS 317J3L							
	SUS 836L		N08367					
	SUS 890L		N08904	N08904	904S14		Z2NCDU25-20	
	SUS 321	1Cr18Ni9Ti 0Cr18Ni10Ti	S32100	321	321S31	X6CrNiTi18 10	Z6CNT18-10	08X18H10T
	SUS 347	0Cr18Ni11Nb	S34700	347	347S31	X6CrNiNb18 10	Z6CNNb18-10	08X18H12B
	SUS 384		S38400	384			Z6CN18-16	
	SUS XM7	0Cr18Ni9Cu3	S30430	304Cu	394S17		Z2CNU18-10	
	SUS XM15J1	0Cr18Ni13Si4	S38100				Z15CNS20-12	
	SUS 329J1	0Cr26Ni5Mo2	S32900	329				
	SUS 329J3L		S39240	S31803			Z3CNDU22-05Az	08X21H6M2T
	SUS 329J4L		S39275	S31260			Z3CNDU25-07Az	

Technical information



R14

Material cross reference table

Steel

Classification	Japan	China	USA		UK	Germany	France	Russia
	JIS	GB	UNS	AISI	BS	DIN	NF	ГОСТ
Stainless steel	SUS 405	0Cr13Al 0Cr13	S40500	405	405S17	X6CrAl13	Z8CA12	
	SUS 410L	00Cr12					Z3C14	
	SUS 429		S42900	429				
	SUS 430	1Cr17	S43000	430	430S17	X6Cr17	Z8C17	12X17
	SUS 430F	Y1Cr17	S43020	430F		X7CrMoS18	Z8CF17	
	SUS 430LX		S43035			X6CrTi17	Z4CT17	
	SUS 430J1L					X6CrNb17	Z4CNb17	
	SUS 434	1Cr17Mo	S43400	434	434S17	X6CrMo17 1	Z8CD17-01	
	SUS 436L		S43600	436				
	SUS 436J1L							
	SUS 444		S44400	444			Z3CDT18-02	
	SUS 447J1	00Cr30Mo2	S44700					
	SUS XM27	00Cr27Mo	S44627				Z1CD26-01	
	SUS 403	1Cr12	S40300	403				
	SUS 410	1Cr13	S41000	410	410S21	X10Cr13	Z13C13	
	SUS 410S		S41008	410S	403S17	X6Cr13	Z8C12	08X13
	SUS 410F2							
	SUS 410J1	1Cr13Mo 1Cr12Mo	S41025			X12CrS13		
	SUS 416	Y1Cr13	S41600	416	416S21		Z11CF13	
	SUS 420J1	2Cr13	S42000	420	420S29	X20Cr13	Z20C13	20X13
	SUS 420J2	3Cr13	S42000	420	420S37	X30Cr13	Z33C13	30X13
	SUS 420F	Y3Cr13	S42020	420F			Z30CF13	
	SUS 420F2							
	SUS 429J1							
	SUS 431	1Cr17Ni2	S43100	431	431S29	X20CrNi17 2	Z15CN16-02	20X17H2
	SUS 440A	7Cr17	S44002	440A			Z70C15	
	SUS 440B	8Cr17	S44003	440B				
	SUS 440C	9Cr18 11Cr17 9Cr18Mo	S44004	440C			Z100CD17	95X18
	SUS 440F	Y11Cr17	S44020	S44020				
	SUS 630	0Cr17Ni4CuNb	S17400	S17400		X5CrNiCuNb16-4	Z6CNU17-04	
	SUS 631	0Cr17Ni7Al	S17700	S17700		X7CrNiAl17 7	Z9CNA17-07	09X17H7 IO
	SUS 632J1							

Representative classification of stainless steel

Stainless steel (Austenitic related)

JIS	
SUS201	SUS309S
SUS202	SUS310S
SUS301	SUS316
SUS302	SUS316L
SUS302B	SUS316N
SUS303	SUS317
SUS303Se	SUS317L
SUS304	SUS321
SUS304L	SUS347
SUS304N1	SUS384
SUS304N2	SUSXM7
SUS305	SUSXM15J1
SUS308	

Stainless steel (Ferritic related)

JIS
SUS405
SUS429
SUS430
SUS430F
SUS434
SUSXM27

Stainless steel (Precipitation hardening)

JIS
SUS630
SUS631

Stainless steel (Martensitic related)

JIS
SUS403
SUS410
SUS410S
SUS416
SUS420J1
SUS420F
SUS431
SUS440A
SUS440B
SUS440C
SUS440F

R



Technical information

R15

Material cross reference table

Steel

Classification	Japan	China	USA		UK	Germany	France	Russia
	JIS	GB	UNS	AISI	BS	DIN	NF	ГОСТ
Heat-resisting steel	SUH 31				331S42		Z35CNWS14-14	45X14H14B2M
	SUH 35				349S52		Z52CMN21-09Az	
	SUH 36	5Cr21Mn9Ni4N	S63008		349S54	X53CrMnNi21 9	Z55CMN21-09Az	55X20 Г 9AH4
	SUH 37	2Cr21Ni12N	S63017		381S34			
	SUH 38							
	SUH 309	2Cr23Ni13	S30900	309	309S24		Z15CN24-13	
	SUH 310	2Cr25Ni20	S31000	310	310S24	CrNi2520	Z15CN25-20	20X25H20C2
	SUH 330	1Cr16Ni35	N08330	N08330			Z12NCS35-16	
	SUH 660	0Cr15Ni25Ti2MoAlVB	S66286				Z6NCTV25-20	
	SUH 661		R30155					
	SUH 21					CrAl1205		
	SUH 409		S40900	409	409S19	X6CrTi12	Z6CT12	
	SUH 409L						Z3CT12	
	SUH 446	2Cr25N	S44600	446			Z12C25	15X28
	SUH 1	4Cr9Si2	S65007		401S45	X45CrSi9 3	Z45CS9	
	SUH 3	4Cr10Si2Mo					Z40CSD10	40X10C2M
	SUH 4	8Cr20Si2Ni			443S65		Z80CSN20-02	
	SUH 11							40X 9C2
	SUH 600	2Cr12MoVNbN						20X12BHMБФР
	SUH 616	2Cr12NiMoWV	S42200					

Representative classification of heat-resistant steel

Heat-resistant steel (Austenitic related)

JIS
SUH31
SUH35
SUH36
SUH37
SUH38
SUH309
SUH310
SUH330
SUH660
SUH661

Heat-resistant steel (Ferritic related)

JIS
SUH21
SUH409
SUH446

Heat-resistant steel (Martensitic related)

JIS
SUH1
SUH3
SUH4
SUH11
SUH600
SUH616

R



Technical information

R16

Material cross reference table

Steel

Classification	Japan	China	USA	UK	Germany	France	Russia
	JIS	GB	AISI/ASTM	BS	DIN	NF	ГОСТ
Carbon tool steel	SK140 (SK1)	T13				C140E3U	Y13
	SK120 (SK2)	T12	W1-11½			C120E3U	Y12
	SK105 (SK3)	T11	W1-10		C105W1	C105E2U	Y11
	SK95 (SK4)	T10	W1-9			C90E2U	Y10
	SK85 (SK5)	T8Mn T9	W1-8		C80W1	C90E2U C80E2U	Y8Г Y9
	SK75 (SK6)	T8			C80W1	C80E2U C70E2U	Y8
	SK65 (SK7)	T7			C70W2	C70E2U	Y7
High speed tool steel	SKH2	W18Cr4V	T1	BT1		HS18-0-1	P18
	SKH3	W18Cr4VC05	T4	BT4	S18-1-2-5	HS18-1-1-5	P18K5Ф2
	SKH4	W18Cr4V2Co8	T5	BT5		HS18-0-2-9	P18K5Ф
	SKH10	W12Cr4VC05	T15	BT15	S12-1-4-5	HS12-1-5-5	
	SKH51	W6Mo5Cr4V2	M2	BM2	S6-5-2	HS6-5-2	P6M5
	SKH52	CW6Mo5Cr4V2 W6Mo5Cr4V3	M3-1				P6M5Ф3
	SKH53	CW6Mo5Cr4V3	M3-2		S6-5-3	HS6-5-3	P6M5Ф3
	SKH54		M4	BM4		HS6-5-4	
	SKH55	W6Mo5Cr4V2Co5 W7Mo5Cr4V2Co5	M35 M41	BM35	S6-5-2-5	HS6-5-2-5HC	P6M5K5
	SKH56		M36				
	SKH57			BT42	S10-4-3-10	HS10-4-3-10	
	SKH58	W2Mo9Cr4V2	M7			HS2-9-2	
	SKH59	W2Mo9Cr4VC08	M42	BM42	S2-10-1-8	HS2-9-1-8	
Alloy tool steel	SKS11		F2				XB4
	SKS2				105WCr6	105WCr5	XБГ
	SKS21	W					
	SKS5						
	SKS51		L6				
	SKS7						
	SKS8	Cr06				C140E3UCr4	13Х
	SKS4	5CrW2Si 6CrW2Si	S1				6ХВ2С 5ХВ2СФ
	SKS41	4CrW2Si	S1				4ХВ2С
	SKS43		W2-9½	BW2		100V2	
	SKS44		W2-8				
	SKS3	9CrWMn					9ХВГ
	SKS31	CrWMn			105WCr6	105WCr5	XБГ
	SKS93						
	SKS94						
	SKS95	8MnSi					
	SKD1	Cr12	D3	BD3	X210Cr12	X200Cr12	X12
	SKD10	Cr12Mo1V1	D2		X153CrMoV12		X12MФ
	SKD11	Cr12MoV	D2	BD2	X153CrMoV12	X160CrMoV12	
	SKD12	Cr5Mo1V	A2	BA2		X100CrMoV5	
	SKD4					X32WCrV3	
	SKD5	3Cr2W8V	H21	BH21	X30WCrV9-3	X30WCr9	
	SKD6	4Cr5MoSiV	H11	BH11	X38CrMoV51	X38CrMoV5	4Х5MФC
	SKD61	4Cr5MoSiV1	H13	BH13	X40CrMoV51	X40CrMoV5	4Х5MФ1C
	SKD62		H12	BH12		X35CrWMoV5	3Х3M3Ф
	SKD7	4Cr3Mo3SiV	H10	BH10	X32CrMoV33	32CrMoV12-18	
	SKD8		H19	BH19			
	SKT3					55CrNiMoV4	
	SKT4	5CrNiMo		BH224/5	55NiCrMoV6	55NiCrMoV7	5XHM

R



Technical information

R17

Material cross reference table

Steel

Classification	Japan	China	USA	UK	Germany	France	Russia
	JIS	GB	AISI/ASTM	BS	DIN	NF	ГОСТ
Spring steel	SUP3		1075 1078				75 80 85
	SUP6	55Si2Mn			56SiCr7	60Si7	60C2
	SUP7	60Si2Mn 60Si2MnA	9260		61SiCr7	60Si7	60C2Г
	SUP9	55CrMnA	5155		55Cr3	55Cr3	
	SUP9A	60CrMnA	5160		55Cr3	60Cr3	
	SUP10	50CrVA	6150	735A51, 735H51	50CrV4	51CrV4	XФА50ХГФА
	SUP11A	60CrMnBA	51B60		51CrV4		50ХР
	SUP12		9254	685A57, 685H57	54SiCr6	54SiCr6	
	SUP13	60CrMnMoA	4161	705A60, 705H60	60CrMn3-2	60CrMo4	
Free cutting carbon steel	SUM11		1110				
	SUM12	Y12	1108				
	SUM21		1212				
	SUM22	Y15	1213	(230M07)	9SMn28	S250	
	SUM22L	Y12Pb	12L13		9SMnPb28	S250Pb	
	SUM23		1215				
	SUM23L						
	SUM24L	Y15Pb	12L14		9SMnPb28	S250Pb	
	SUM25				9SMn36	S300	
	SUM31		1117		15S10		
	SUM31L						
	SUM32	Y20		210M15, 210A15		(13MF4)	
	SUM41	Y30 Y35	1137			(35MF6)	
	SUM42	Y40Mn	1141			(45MF6.1)	
	SUM43		1144	(226M44)		(45MF6.3)	
High carbon chromium bearing steel	SUJ1	GCr4	51100				
	SUJ2	GCr15	52100		100Cr6	100Cr6	ШХ15
	SUJ3	GCr15SiMn	ASTM A 485 Grade 1				
	SUJ4	GCr15SiMo					
	SUJ5	GCr18Mo					

R



Technical information

R18

Material cross reference table

Cast iron

Classification	Japan	China	USA	UK	Germany	France	Russia
	JIS	GB	AISI/SAE	BS	DIN	NF	ГОСТ
Gray cast iron	FC100	HT100	N0.20	100	GG10		СУ10
	FC150	HT150	N0.30	150	GG15	FGL150	СУ15
	FC200	HT200	N0.35	200	GG20	FGL200	СУ20
	FC250	HT250	N0.45	250	GG25	FGL250	СУ25
	FC300	HT300	N0.50	300	GG30	FGL300	СУ30
	FC350	HT350	N0.60	350	GG35	FGL350	СУ35
					GG40	FGL400	СУ40
Nodular cast iron	FCD400	QT400-18	60-40-18	400/17	GGG40	FGS370-17	BY40
	FCD450	QT450-10	65-45-12	420/12		FGS400-12	BY45
	FCD500	QT500-7	70-50-05	500/7	GGG50	FGS500-7	BY50
	FCD600	QT600-3	80-60-03	600/7	GGG60	FGS600-2	BY60
	FCD700	QT700-2	100-70-03	700/2	GGG70	FGS700-2	BY70
	FCD800	QT800-2	120-90-02	800/2	GGG80	FGS800-2	BY80
		QT900-2		900/2			BY100

Non-ferrous metals

Classification	Japan	China	USA	UK	Germany	France	Russia
	JIS	GB	ASTM	BS	DIN	NF	ГОСТ
Aluminum alloys		1A99	1199		A199.99R		A99
		1A97			A199.98R		A97
		1A95					A95
	A1080	1A80		1080(1A)	A199.90	1080A	A8
	A1050	1A50	1050	1050(1B)	A199.50	1050A	A5
	A5052	5A02	5052	NS4	AlMg2.5	5052	AMg
		5A03		NS5			AMg3
	A5056	5A05	5056	NB6	AlMg5		AMg5V
	A5556	5A30	5456	NG61		5957	
	A2117	2A01	2036		AlCu2.5Mg0.5	2117	D18
	A2017	2A11		HF15	AlCuMg1	2017S	D1
	A2024	2A12	2124		AlCuMg2	2024	D16AVTV
		2B16	2319				
	A2N01	2A80					AK4
	A2018	2A90	2218				AK2
	A2014	2A14	2014		AlCuSiMn	2014	AK8
	A7075	7A09	7175		AlZnMgCu1.5	7075	V95P
Aluminum alloy casting	AC4C	ZAlSi7Mn	356.2	LM25	G-AlSi7Mg		
	AC3A	ZAlSi12	413.2	LM6	G-Al12	A-S12-Y4	AL2
		ZAlSi5Cu1Mg	355.2				AL5
	AC8A	ZAlSi2Cu2Mg1	413.0		G-Al12(Cu)		
		ZAlCu5Mn					AL19
		ZAlCu5MnCdVA	201.0				
		ZAlMg10	520.2	LM10	G-AlMg10	AG11	AL8
		ZAlMg5Si			G-AlMg5Si		AL13

R



Technical information

R19

Insert grade cross reference table

CVD Coated Carbide (Turning)

This table is Kyocera's own estimation based on publications and is not authorized by companies mentioned in it.

Classification		Kyocera	Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
	Symbol											
P (Steel)	P01	CA510 CA5505	JC110V	HG8010 HG5000 HG3305	UE6105 UE6005 UE6015		GC4305 GC4005 GC4205	TP0501 TP0500 TP1000	AC700G AC810P	T9005 T9105	KCPK05 KCP05B KC9105	IC8150 IC9150
	P10	CA510 CA515 CA5505 CA5515	JC110V JC215V	GM10 GM20 GM8015 HG8010	MC6105 MC6115 UE6105 UE6110 UE6010 UE6020	CP2 CP5 CP7	GC4415 GC4205 GC4015 GC3115 GC4215 GC4315	TP1501 TP1000 TP1500 TP100	AC700G AC2000 AC810P AC820P AC8015P AC8025P	T9005 T9105 T9015 T9115 T9215	KCK05 KCP10B KC910 KC9110	IC8150 IC9150
	P20	CA025P CA525 CA5515 CA5525 CR9025	JC110V JC215V	GM20 GM8020 HG8025	MC6125 MC6025 UC6010 UE6110 UE6020	CP2 CP5 CP7	GC4425 GC4215 GC4220 GC4225 GC4325	TP2501 TP2000 TP2500 TP200	AC2000 AC3000 AC820P AC830P AC8020P	T9015 T9115 T9025 T9125 T9225	KCP25B KCP25 KC9125 KC9225 KC9325	IC8250 IC9125 IC9250 IC9350
	P30	CA025P CA525 CA5525 CA530 CA5535 CR9025	JC215V JC325V	GM25 GM8035 HG8025	MC6125 MC6025 UE6020 MC6035 UE6035 UH6400		GC4425 GC4225 GC4230 GC4235 GC2135 GC4335	TP2501 TP3501 TP2500 TP2000 TP3500 TP200	AC3000 AC630M AC830P ACP100 AC8035P	T9125 T9035 T9135 T3130	KCP30B KCP30 KC9040 KC9140	IC635 IC8350 IC9350
	P40	CA530 CA5535	JC325V JC450V JC540V	GX30	MC6035 UE6035 UH6400		GC4035 GC4235 GC4240 GC4335	TP40	AC630M AC830P ACP100	T9035 T3130	KCP40B KCP40 KC9140 KC9240	IC635
M (Stainless steel)	M10	CA6515	JC605X JC110V	GM10 HS9105	MC7015 US7020	CP2 CP5	GC2015 GC2220	TM1501 TP1500 TP100	AC610M AC6020M	T9015 T9115 T6215	KCM15B KCM15 KC9010 KC9110 KC9210	IC8250 IC9250 IC9350 IC6015
	M20	CA6525	JC110V JC215V	GM8020 HG8025 HS9115	US7020 MC7025	CP2 CP5	GC1515 GC2015 GC2025 GC2220	TM2501 TM2000 TP200	AC6020M AC6030M AC610M AC630M AC830P	T6020 T6120 T9115 T9125	KCM25B KCM25 KC9025 KC9125 KC9225	IC8350 IC9250 IC9350 IC6025
	M30		JC215V JC325V JC525X	GM25 GM8035	MC7025 US735		GC2040 GC235	TM4000 TP3501 TP300	AC6030M AC630M AC830P	T6030 T6130 T9125	KCM35B KCM35 KC9240	IC8350 IC9350 IC4050
	M40		JC525X	GX30 IP100S	US735			TP40			KC9045 KC9245	IC635
K (Cast iron)	K01	CA310 CA4505 CA5505	JC105V JC605W JC050W	HG3305 HG3315 HX3505 HX3515	MC5005 UC5105 UC5015	CP1	GC3205 GC3210	TK0501 TK1000 TK1001	AC405K AC410K AC300G AC410K	T505 T5105 T5010	KCPK05 KC9315 KCK05B KCK05	IC5005 IC428 IC9007 IC9150
	K10	CA310 CA315 CA4505 CA4515 CA5505	JC050W JC110V JC605W JC108W	GM8015 HX3515 HG8010 HG3315	UC5015 UC5105 UC5115 UE6010 MC5015	CP1 CP2 CP5	GC3205 GC3210 GC3215 GC3115	TK1501 TK1000 TK2000 TK2001 MK1500	AC4010K AC410K AC415K AC700G AC4015K	T515 T5105 T5115 T5010	KC9110 KC9120 KC9315 KCK15B KCK15	IC5010 IC418 IC428 IC9015 IC9007
	K20	CA315 CA320 CA4515	JC110V JC215V JC108W JC605W	GM8020 HG8025	MC5015 MY5015 UE6010 UC5115 UE6110	CP2 CP5	GC4225 GC3215 GC3220 GC3225	TK2000 TX150 TP200	AC4015K AC420K AC700G AC820P	T515 T5115 T5125 T5020	KC9125 KC9320 KC9325 KCK20B KCK20	IC418 IC9015
	K30	CA320	JC215V	GM25	UE6110		GC3040 GC4335	TP2500 TP200		T5125 T9125	KCP25B KC9320	

Technical information



R

R20

Insert grade cross reference table

PVD Coated Carbide (Turning)

This table is Kyocera's own estimation based on publications and is not authorized by companies mentioned in it.

Classification		Kyocera	Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
	Symbol											
P (Steel)	P01	PR1705	JC5003						ACZ150		KC5510	
	P10	PR1705 PR930 PR1025 PR1115 PR1215 PR1225 PR1725	JC5003 JC5030	CY15 CY150 IP2000	MS6015 VP10MF	VM1 TM1 TA1 TAS DT4 DM4	GC1025	CP200	ACZ150 ACZ310 AC520U	AH710	KC5010 KC5510 KU10T	IC507 IC807 IC907 IC1010
	P20	PR930 PR1025 PR1115 PR1215 PR1225 PR1625 PR1725	JC5015 JC5030 JC5040	CY150 IP2000	MS6015 VP10RT VP15TF VP20MF UP20M VP20RT	QM1 VM1 TA1 TAS TM4	GC1020 GC1025 GC4125 GC1125	CP250	ACZ310 ACZ330 AC520U	AH7025 AH710 AH725 AH730 SH725 SH730	KC5025 KC5525 KC7215 KC7315 KU25T	IC507 IC907 IC908
	P30	PR1025 PR1225 PR1535	JC5015 JC5040	CY250 CY9020 HC844 IP3000	VP10RT VP15TF VP20MF UP20M MS7025	ZM3 QM3 TAS	GC1125 GC1145 GC1115 GC1105	CP500	ACZ330 ACZ350 AC530U AC1030U	GH330 AH120 AH740 AH9030	KC7015 KC7020 KC7235 KU25T	IC328 IC928 IC3028 IC1030
	P40	PR1535	JC5040	CY250 HC844		ZM3 QM3 TAS	GC1145 GC2145	CP600	ACZ350	AH140 AH740 J740	KC7030 KC7040 KC7140	IC328 IC3028
M (Stainless steel)	M10	PR1025 PR1215 PR1225	JC5003	IP050S JP9105	VP10MF VP10RT	VM1 TM1 TA1	GC1005 GC1025 GC1105 GC15	TS2000 CP200 CP250	EH510Z ACZ150 AC510U	AH710	KC5010 KC5510 KC6005 KCU10	IC507 IC520 IC807 IC907
	M20	PR930 PR1025 PR1125 PR1215 PR1725 PR1225 PR1515	JC5015 JC5030 JC5040 JC8015 JC5118	IP100S GX30 JP9115	MS9025 VP10RT VP15TF VP20MF UP20M VP20RT MS7025	ST4 QM1 VM1 TA1 TM4 TAS DT4 DM4	H5D6 GC1025 GC1115 GC4125 GC1125 GC30	TTP2050 TS2500 CP200 CP250 CP500	EH520Z ACZ150 ACZ310 AC520U AC1030U	AH6225 AH630 AH725 AH730 GH330 GH730 SH725 SH730	KC5025 KC5525 KC7020 KC7025 KCU25	IC308 IC507 IC907 IC908 IC3028
	M30	PR1125 PR1535	JC5015 JC5030 JC5040 JC5118	CY250 CY9020	VP15TF VP20MF UP20M MP7035	ST4 ZM3 QM3 TAS	GC1020 GC2035 GC2030	CP500	ACZ330 ACZ350 AC530U AC6040M	AH6030 AH120 AH725 AH6235	KC7030 KC7225	IC1030 IC908 IC1008 IC1028 IC3028
	M40	PR1535	JC5118		MP7035	ZM3 QM3 TAS	GC2145 GC1145	CP600	AC6040M ACZ350	J740 AH140 AH645		IC228 IC928 IC328
K (Cast iron)	K01		JC5003						EH10Z	AH110	KC5515	IC910
	K10	PR905 PR1215	JC5003 JC5015	CY100H CY10H	VP05RT	TA1 TM1	GC1010	TS2000 CP200	EH10Z EH510Z AC510U	GH110 AH110	KC5010 KC7210	IC1010 IC807 IC910 IC908
	K20	PR905 PR1215	JC5015	IP2000 CY9020	VP10RT VP15TF VP20RT	QM1 TA1	GC1020 GC1120	TS2500 CP200 CP250	EH20Z ACZ310 AC520U AC530U AC1030U	AH120 AH725	KC5025 KC5525 KC7015 KC7215 KC7315	IC508 IC908
	K30				VP15TF VP20RT	QM3 TA3	GC1030	CP500	ACZ310		KC7225	IC508 IC908
S (Difficult-to-cut material)	S01	PR005S	JC5003		MP9005 VP05RT				AC5005S	AH8005 AH905		IC804 IC806
	S10	PR005S PR015S	JC5015 JC8015	JP9105	MV9005 MP9005 MP9015 VP10RT		GC1105 GC1005 GC1025	TH1000 CP200 TS2000	AC510U AC5015S	AH8015 AH905 SH730 AH110	KC5010 KC5510 KCU10 KCS10	IC1010 IC808 IC907 IC908
	S20	PR015S PR1535	JC5015 JC8015	JP9115	MP9015 MT9015 VP20RT MS9025		GC1025 GC1125	CP250 TS2500	AC510U AC520U AC5025S	AH8015 AH120 AH725	KCS10B KC5025 KC5525 KCU25	IC806 IC808 IC908
	S30	PR1535			MP9025		GC1125		AC520U	AH725		IC3028

R



Technical information

R21

Insert grade cross reference table

Cermet (Turning)

This table is Kyocera's own estimation based on publications and is not authorized by companies mentioned in it.

Classification		Kyocera	Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
	Symbol											
P (Steel)	P01	TN610 PV710	LN10 CX50	CH350	AP25N VP25N NX1010	T3N T15 Q15			T110A T1000A	NS520 GT530 GT720 J530	KT1120 KT125 HTX	IC20N IC520N
	P10	TN610 TN620 TN6020 TN60 PV710 PV720 CCX	LN10 CX50 CX75 NIT PX75	CH350 CZ25	NX2525 AP25N VP25N	T15 C7Z Z15	CT5015 CT525	TP1020 CM CMP	T1500Z T2000Z T1200A T1500A	NS9530 NS520 GT530 GT530 GT730 AT9530	KT315 KT175 HT2 KTP10	IC20N IC520N IC530N IC75T
	P20	CCX TN620 TN90 TN6020 PV720	CX50 CX75 CX90 NAT PX90	CH550 CH7030 CZ1025 CZ25	MP3025 NX2525 NX3035 AP25N VP45N	T15 C7X C7Z	CT525 CT530 GC1525	TP1020 C15M TP1030	T1200A T1500A T2000Z T2500Z T3000Z	NS9530 NS530/730 GT530 GT530/730 AT9530	PS5 KT5020	IC20N IC520N IC530N IC75T IC30N
	P30	PV730	CX90 CX99 SUZ		NX4545 VP45N	N40 C7X	CT530 GC1525	TP1030	T3000Z T250A	NS740		IC75T IC30N
M (Stainless steel)	M10	TN620 TN60 TN6020 PV720	LN10	CH350	NX2525 AP25N VP25N	T15 C7X C7Z Z15	CT5015 CT525	CM CMP	T110A T1000A T2000Z	NS520 J530	KT1120 KT315 KT125	IC20N IC520N
	M20	TN620 TN90 TN6020 PV720	CX50 CX75 PX75 NIT NAT	CH550 CH7030 CZ1025	NX2525 NX3035 AP25N VP25N	C7X C7Z Q15	CT530 GC1525	TP1020 C15M	T1500A T2000Z	NS530 NS730 GT530 GT730	KT175 HT2 PS5 KT5020	IC30N IC530N
	M30	PV730	CX75 CX90 PX90 CX99 SUZ	CZ25	NX4545	C7X		TP1030	T3000Z T250A	NS740		
K (Cast iron)	K01	PV7005 CCX	LN10		AP25N VP25N	T3N T15 Q15			T110A T1000A	NS520	KT1120	
	K10	TN610 CCX PV710 PV7005	LN10	CH350	NX2525 AP25N VP25N	T15 C7X C7Z Z15	CT5015		T1200A T1500A T2000Z	NS530 NS730 GT530 GT730	KT315 HTX KTP10	
	K20		NIT	CZ25	NX2525 AP25N VP25N				T3000Z		KT5020	

Boldface grade shows PVD Coated Cermet. (CCX is CVD Coated Cermet grade)

Carbide

Classification		Kyocera	Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
	Symbol											
P (Steel)	P10		SRT	WS10	STi10T		S1P		ST10P	TX10S	K2885	IC70
	P20		SRT DX30	EX35	STi20 UTi20T		SMA	S10M	ST20E	TX20 TX25	K125M	IC70 IC50M
	P30		SR30 DX30 DX35	EX35 EX40	UTi20T		SM30	S25M	A30N A30 ST30E	TX30 UX30	KMF	IC50M IC54
	P40		SR30 DX35	EX45			S6	S60M	ST40E	TX40	PVA	IC54
K (Cast iron)	K01		KG03	WH02 WH05	HTi05T		H1P		H1 H2	TH03 KS05F	K68 K10	IC04
	K10	KW10 GW15	KG10 KT9	WH10	HTi10	KM1	H1P H10 HM	890	EH10 EH510	G1F TH10 H10T	KMI K8735 K313	IC20
	K20	GW25	CR1 KG20	WH20	HTi20T UTi20T	KM3	H13A	883 890 HX	G10E EH20 EH520	G2F KS15F KS20	KMF	IC20 IC10
	K30		KG30					883	G3 G10E	G3 UX30	THR	IC10 IC28
V (Wear and shock resistant tool)	V40		G5 GD195	WH50	GTi30				G5	D40		
	V50	VW50	MH3 MH4 GD174 GD201	WH60	GTi35 GTi40 GTi30S				G6	D50		
	V60		MH5 MH7 MH8 GD206	WB60	GTi40S GTi50S				G7 G8	D60		



Insert grade cross reference table

This table is Kyocera's own estimation based on publications and is not authorized by companies mentioned in it.

Classification		Kyocera	Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
	Symbol											
P (Steel)	P10	PR1225	JC5003 JC5030 JC8003 DH103	JP4105 JX1020 JP4005 PN08N	F7010		GC1025 GC1010		ACP100		KC715M	
	P20	PR1525 PR1225 PR1230 CA520D	DH111 DH110 DH115 JC8015 JC8118 JC7518	JP4120 JS4045 JP4020 TB6020 JX1015 GX2140	MC7020 MP6120 F7030 UP20M MV1020	TM1 DT4 DM4	GC1130 GC1030 GC4220 GC4020 GC4030 GC4334	MP1500 T250M T25M T20M	ACP200 ACP2000 ACU2500 XCU2500	T313W AH725 AH3225	KC522M KC525M KCPM20	IC5500 IC330 IC520M IC950 IC5400 IC1008
	P30	PR1230 PR1535	JC6235 JC5015 JC5040 JC5240 JC8050 JC7550	CY250 CY9020 TB6045 JX1045 JM4060 GX2160	MP6130 F7030 VP15TF VP30RT	ZM3	GC1130 GC4040 GC4230 GC4330	MP2500 T250M T25M F25M F30M	AC230 ACP300 ACP3000	AH9130 T3130 GH330 AH330 AH730 AH3135	KC994M KC725M KC792M KC530M KCPK30 KCPM40	IC330 IC328 IC635 IC830 IC908 IC928
	P40		JC7550 JC5040 JC7560	CY250 HC844 TB6060 JX1060	VP30RT		GC4040 GC4240 GC4340	MP3000 T350M T60M T25M	AC230 ACZ330 ACZ350	AH140	KC735M	IC635 IC928 IC4050
M (Stainless steel)	M10	PR1225	DH108 DH111	CY9020 JX1020 JP4020	F7010		GC1025 GC1030		ACM100 ACM200 EH10Z		KC522M	
	M20	PR1525 PR1225	JC730U JC835S JC8118 JC5015 JC5030 JC5040 JC7518	PN215 CY150 TB6020 JX1015 CY250	MV1020 MC7020 F7030 VP15TF VP20RT MP7030 MP7130	DT4 DM4	GC2030 S30T GC2334 GC2044	MS2050 MP2500 T250M T25M F20M F25M F30M	XCU2500 ACM200 ACP200 EH20Z ACU2500 AH3225	GH330 AH330 AH120 AH130 AH725 AH3135	KC730M KC525M	IC380 IC908 IC928 IC882
	M30	CA6535 PR1535	JC835S JC8015 JC5015 JC5118 JC8050	JM4160 JM4060 TB6045 JX1045 GX2160	F7030 VP30RT MP7140	ZM3	GC1040 GC2040 S40T	T350M T250M F40M	ACM300 ACP300 ACZ350	T3130 AH130 AH9130	KC994M KC725M KCPK30	IC380 IC328 IC330
	M40		JC7560		VP30RT			MM4500	ACZ350	AH140		IC830
K (Cast iron)	K01		DH202 DH102	TB6005				MH1000	ACK100	AH110		IC5100 IC4100
	K10	PR1510 PR905 PR1210	DH103 JC8015 JC610 JC605W JC8118	JP4005 CY10H CY100H CY9020	MP8010 MC5020 VP10RT MV1020		GC1010 GC3220 K15W	MK1500 T150M F15M	XCK2000 ACK2000 ACK200 AC211 ACU2500	T1015 T1115 AH110 T1215	KCKP10 KCK15 KC915M	IC5100 IC4010 IC910 DT7150 IC810
	K20	CA420M PR905 PR1210 CA415D	JC605X JC610 JC5015 JC8015 JC8118	TH315 CY150 TB6020 JX1015	VP15TF VP20RT		GC1020 GC3020 K20W/K20D GC3330 GC3344	MP1500 T150M T250M MK2000 MK2050	EH20Z ACZ310 ACK300 ACK3000	AH120 AH725 T1215	KCK20B KC520M KC920M KC925M KC992M	IC810 IC910 IC928
	K30		JC5080 JC6235				GC3040 GC4040	MK3000 T250M		AH9130 GH130	KC930M	IC928
S (Difficult-to-Cut Material)	S10	CA6535 PR1535 PR1210	DH202 DH102 DH103 JC7518	PCS08M PTH13S JS1025	MP9120 VP15TF		GC1030 GC1025 GC1010	MS2050	ACM100 ACM200 ACK300	AH8015	KC510M	IC903 IC807 IC808 IC908
	S20	CA6535 PR1535 PR1210	DH111 JC8118 JC5015 JC8050 JC7560 JC7550	CY100H CY10H	MP9120 VP15TF MP9130 MP9030		GC1030 GC2030 S30T GC1130 GC4344	MP2050	ACU2500 ACM200		KC522M KC525M KCSM30	IC882 IC903 IC808 IC908 IC830 IC928
	S30	PR1535	JC8050 JC7560		MP9140		GC2040 S40T	F40M	ACM300		KC725M KCSM40	IC328 IC330

R



Technical information

R23

Insert grade cross reference table

Cermet (Milling)

This table is Kyocera's own estimation based on publications and is not authorized by companies mentioned in it.

Classification		Kyocera	Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
	Symbol											
P(Steel)	P10	TN60 TN620M PV60M	NIT CX75	CH550 MZ1000	NX2525			C15M		NS530 NS730	KT530M KT195M	
	P20	TN620M TN100M TN60 PV60M	NAT CX75 CX90	CH570 CH7030	NX2525 MX3020	C7X C7Z	CT530	C15M MP1020	T2500A T250A T1500A	NS530 NS730 NS740	HT7 KT530M KT605M	IC30N
	P30		CX90 CX99 SC30	CH7035	NX4545 MX3030				T4500A	NS540		IC30N
M(Stainless steel)	M10	TN60 TN620M PV60M		MZ1000	NX2525			C15M				
	M20	TN620M TN100M TN60 PV60M	NIT CX75 NAT	CH550 CH570 CH7030	NX2525		CT530	C15M	T2500A T250A	NS530	KT7 KT530M KT605M	IC30N
	M30		CX75 CX90 CX99 SC30		NX4545				T4500A	NS740 N308		
K(Cast Iron)	K01		LN10									
	K10	PV60M	LN10 CX75	MZ1000 CH550	NX2525							IC30N
	K20		NIT	CH7030 CH7035	NX2525							

Boldface grade shows PVD Coated Cermet.

Ceramic

Classification		Kyocera	Dijet	Nippon Tungsten	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
	Symbol											
K(Cast Iron)	K01	KA30 A65 KT66 PT600M CS7050 KS6015		NPC-H2 NPC-A2		SE1 HC1 HC2 HC5 HC6 HW2	CC620 CC650		NB90S NB90M WX120	TZ120	KW80 KY1615 AC5	IN11 IS6
	K10	KS6015 A65 KT66 A66N PT600M CS7050 KS6050		NX NXA Whiskal WIN		WA1 HC2 HC6 HC7	CC6090 CC6190 GC1690		WX120 NS260C	LX11 LX21	KYK10 KYK25 KB90 KY1320 KY3000 KY3400	IN420 IN22 IN23 IS80
	K20	KS6050				SX6 SX9 SP9	CC6090 CC6190 GC1690		WX120	WG300 FX105 CX710	KYK35 KY3400 KY3500	IS8
S(Difficult-to-cut material)	S01					JP0	CC650				KY2100	
	S10	KS6030 KS6040	CA200	Whiskal WIN		JX1 JP2 WA1 WA5 SX3 SX7 SX9	CC670 CC6060 CC6065 CC6160		WX120	WG300	KYHK15B KYS25 KY4300 KY1525 KY1540	IS25 IS9
	S20					JX3	CC6220 CC6230		WX120		KYS30	IS35 IW7
H(Hard materials)	H01	A65 KT66 A66N PT600M		NPC-A2		HX5 HC4 HC7 ZC7	CC650 CC670 CC6050		NB100C	LX10 LX11 LX21	KY4400	
	H10	A65 KT66 A66N PT600M		NPC-A2 Whiskal WIN		ZC7 WA1 WA5	CC670			WG300	KY4300 KYHK15B	

Boldface grade shows PVD Coated Ceramic.

R
Technical information



Insert grade cross reference table

CBN

This table is Kyocera's own estimation based on publications and is not authorized by companies mentioned in it.

Classification		Kyocera	Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
	Symbol											
K (Cast iron)	K01	KBN475	JBN795		BC5110	B20 B22 B30	CB7525 CB50 CB7050	CBN050C CBN300P	BN500 BNC500	BX910 BX930 BX950		IB50 IB85
	K10	KBN60M KBN900	JBN330	BH200	MB710 MB5015 MB4020	B22 B23	CB50 CB7050	CBN20 CBN200 CBN300	BNC8115 BN700 BN7000	BX950 BXC90 BX470	KB1630 KB1345 KB9610	IB55 IB90
	K20	KBN900		BH250	MB4120 MBS140 BC5030	B16 B40		CBN350 CBN500 CBN600	BN7000 BNS800	BX950 BXC90 BX90S	KB9640	
H (Hard materials)	H01	KBN510 KBN05M KBN10M KBN020	DH102		BC8105 BC8210 BC8110 MBC010 MB810	B24 B52 B5K	CB20	CBN050C CBN100 CBN10 CBN100 CH0550	BN1000 BNC100 CBN10 BNC2010 BNC2115	BXA10 BXA30 BNC160 BXC30 BXM10	KB1610	IB20H IB25HC IB50
	H10	KBN510 KBN525 KBN05M KBN10M KBN25M KBN020	JC6102 JC8003 JBN500 JBN300 JBN330	BH200	BC8120 MBC020 BC8020 MB8025 MB825	B24 B36 B54 B52 B5K	CB7015 CB7050 CB50 CB7105	CBN150 CBN060K CBN200 CBN160C CK2065	BNC160 BNX20 BN2000 BNC200 BNC2020 BNC2125	BXM10 BXA10 BXA40 BX360 BXC50 BXA20	KBH10 KBH10B KB1615 KB1625 KB5610 KB9610	IB10HC IB50
	H20	KBN020 KBN25M KBN35M KBN900	JC8003 JC5015 JBN245	BH250	BC8220 BC8120 MBC020 BC8020 MB8025	B22 B36 B6K	CB7025 CB7525 CB7115	CBN350 CBN300P CBN400C CBN500 CH2540	BNX25 BN350 BNC300	BX380 BXC50 BXA20 BR35F	KBH20 KBH20B KB1340 KB5625 KB9640	IB55 IB25HA
	H30	KBN35M KBN900	JBN245	BH250	MB835 BC8130	B40 B6K	CB7125 CB7525 CB7135	CH3515	BNC300 BN350	BX380 BXC50 BXM20 BXA20	KB5630 KB9640	IB55 IB25HA
Sintered steel	-	KBN65B KBN570 KBN65M KBN70M	JBN795 JBN500		MB4120 MB4020			CBN200	BN7115 BN350 BN7000 BN7500	BX450 BX470 BX480	KB5630	IB05S IB10H IB10S

Boldface grade shows PVD Coated CBN.

PCD

Classification		Kyocera	Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
	Symbol											
N (Non-ferrous metals)	N01	KPD001	JDA30 JDA735		MD205	PD1	CD05 CD10	PCD05 PCD10	DA90 DA1000 DA2200	DX180 DX160	PD100 KD1400 KD1405	
	N10	KPD001 KPD010 KPD230 KPD250	JDA40 JDA745		MD220	PD2	CD10	PCD10 PCD20	DA150 DA1000 DA2200	DX140	KD100 KD1400 KD1415	ID5
	N20	KPD001 KPD010 KPD230 KPD250	JDA10 JDA715		MD230			PCD30 PCD30M	DA1000 DA2200	DX110 DX120	KD1425	

R



Technical information

R25

Molded chipbreaker cross reference table

Molded chipbreaker cross reference table

Negative inserts

This table is Kyocera's own estimation based on publications and is not authorized by companies mentioned in it.

Cutting range		Kyocera		Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
		General chip- breaker	Chipbreaker for sticky material /Soft steel										
Carbon steel / Alloy steel	Finishing (with wiper edge)	WF WP	-	-	-	SW	-	WL WF	W-FF2 W-MF2	SEW LUW	AFW FW	FW	WF
	Finishing - Medium (with wiper edge)	WE WQ	-	-	-	MW	-	WM WMX	W-M3 W-MS	GUW	ASW SW	MW	WG
	Finishing	DP GP PP	XF XP	F1 FA FT PF	BE BH FE	F FH FS FY PK FP	UL WM ZF1	XF QF	FF1	FP FB FE SP FA FL LU	TF 01 AS TSF	FF UF FS LF	F3P SF PF
	Finishing - Medium	HQ PQ CQ CJ VC VF	XQ	UA UT	AB B CE CT	SH C SA LP SY	WV WR	LC PF	FF2 MF2	SU EX SJ SX UJ SE	TS NS CB 11 17 27 ZF	K RP FN FM	NF SM
	Medium - Roughing	PG GS PS	XS	UR UB	AE DE AH	MV MP MA MH	Z5 ZW1	XM QM SM SMC PM PMC	M3 MF3	UA UG GE GU	AM DM NM TM ZM	MN	M3P TF PP
	Medium - Roughing High feed rate	PT GT	-	GC PQ	AR AY	GH RP	GS	MR XMR	M5 MR5 MR6	MU UX ME	TH 32Y 32 37	RP RN	R3P NR
	Roughing	Standard PH	-	GG LG GQ	RE	MT Standard	G	Standard 23 HM	MR7	MC MU MX UZ	31 33 F-K THS	PR MG	GN
	Roughing Single-sided High feed rate	PX	-	GS RM UC UP UD	H HX HE TE UE	HV HR HX HZ HL HM	-	QR PR HR	R4 R5 R6 R7 RR6 R57 RP	HG HP MP HF	TU TRS 57 65 TUS	RP RH RM RW	TNM NM
Stainless steel/Difficult-to-cut material	Finishing	MQ SQ	-	SF	BH MP	FS SH FJ LM LS	ZF1	MF	M1	SU EF	SF SS	FP	F3M VL F3S
	Medium - Roughing	MS MU TK SG SX	-	GP SZ	DE SE PV VI	MS MA GM MJ MM ES MH GH GJ RM RS	ZP WS	MM MMC MR XMR SM SMR SF SGF SMC MRR	MF1 MF3 A3 A5 M5 56 R8 RR9 MF4	EG EX MU UP EM	HMM SM SA S SH HRM HPF	P MP MS UP	TF PP M3M R3M
Cast iron	Medium	KQ KG C Standard	-	-	AH VA VY	LK MF Standard	-	KF KM	-	UZ UX UJ	Standard 33 CF	FN	GN
	Roughing	KH GC ZS	-	-	-	GH RK	-	KR KRR	MR9	GZ	CM CH	RP UN	NR
Non-ferrous metals	Medium - Roughing	AH	-	-	-	-	-	AL	95	AG	P	GP MS	PP



Molded chipbreaker cross reference table

Positive inserts

Cutting range		Kyocera		Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
		General chipbreaker	Chipbreaker for sticky material / Soft steel										
Carbon steel / Alloy steel	Minute ap	CF	-	-	-	-	-	-	-	-	01	-	-
	Finishing (with wiper edge)	WP	-	-	-	SW	-	WF WK WM	W-F1 W-F2	LUW SDW	SW	FW	WF
	Finishing	PF DP GP PP VF	XP	ASF	-	FV SQ FP SMG	AZ3 AMX AZ7 FG	PF UF XF	FF1	FB GU FC FK FP LU	PF PSF 23	11 GF UF FP	PF SM
	Finishing - Medium (1)	HQ	XQ	ACB FT	JE	MQ MV LP	AF1	PM UM SMC	F1 M3	LB SF SU SS	PS PSS 24	LF	14
	Finishing - Medium (2)	GK	-	BM	JQ	No Indication	QD CL	PF PMC XM	MF2 M5	US GU	-	-	F3P
	Medium	Standard	-	-	J	MP Standard	AM5 AM3 AZ8	PR UR KM XR	F2	MU SC	PM	GM MP MR	Standard
Stainless steel, Difficult-to-cut material	Finishing - Medium	MQ	-	-	MP	FV SV LM LS MS	-	MF MMC SM MR MM	-	LU	PSS JS PF PSF PS PM	FW FP MW	PF WF F2M
Non-ferrous metals	Finishing - Medium	AP AH	-	ALU	-	AZ	-	AL	AL	AG AW	AL	HP	AF AS

Positive inserts (for automatic lathe)

Cutting range		Kyocera		Dijet	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	NTK	Sandvik	Seco	Sumitomo	Tungaloy	Kennametal	Iscar
Carbon steel / Alloy steel	Minute ap	CF	-	-	-	-	-	-	-	-	01	-	-
	Finishing	PF CK GF SKS	ASF	JQ	FP FV SMG LS-P	AZ7 AMX ZR	PF XF	FF1	SI FC	PF	11 UF FP	PF SM	
	Finishing - Medium	GQ SK	ACB FT	JE	LP AM MV	AM3 YL	PM XM	F1 MF2	SU	PS	LF	14	
	Medium	GK	-	J	MP Standard	QD CL	PR	F2	SC	PM	MF MP	Standard	
Stainless steel	Finishing	MQ	-	MP	FV SV LM	-	MF	-	LU	JS PF PSF	FW FP MW	WF	
Non-ferrous metals	Finishing - Medium	AP AH	ALU AWI	-	AZ	-	AL	AL	AG AW	AL	HP	AF AS	

R



Technical information

Milling insert description cross reference table

Milling insert description cross reference table

This table is Kyocera's own estimation based on publications and is not authorized by companies mentioned in it.

Kyocera	Class	Applications	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	Sandvik	Sumitomo	Tungaloy	Iscar
SDMR1203AUER-H SDKR1203AUEN-S	M K	Steel	SDKR42TN	(SDNR1203AEEN-JS)		SDMR1203AEEN SDMR1203AETN	SDMR1203AETN-MJ SDKR1203AESR-MJ SDKR1203AETN-MJ SDKR1203AEPN-MS SDKR42ZSR-MJ SDKR42ZPN-MS	SDKR1203AUTR-HS SDKR1203AUN-76
SDKN1203AUTN			SDK42TN-C9	SDKN1203AEN SDKN1203AETN (SDNN1203AETN1)		SDKN42MT (SDNN1203AETN)	SDKN1203AETN-12 SDKN42ZTN	SDKN1203AETN
SDKN1203AUFN	K	Cast Iron	SDK42FN-C9			SDKN42M (SDNN1203AEEN)	SDKN1203AEFN-12 SDKN42ZFN	
		Non-ferrous metals				SDKN42M	(SDCN1203AEFN-D) (SDCN42ZFN-DIA)	
SDKN1504AUTN	K	Steel	SDK53TN-C9	SDKN1504AEN SDKN1504AETN		SDKN53MT	SDKN1504AETN SDKN53ZTN	SDKN1504AETN
SEMR1203AFER-H SEKR1203AFEN-S	M K	Steel	SEKR42TN	(SEER1203AFEN-JS)	SEKR1203AZ-WM (SEER1203AZ-WL)	SEMR1203AFEN (SEER1203AFEN)	SEMR1203AFTN-MJ SEKR1203AFSR-MJ SEKR1203AFTN-MJ SEKR1203AFPN-MS	SEKR1203AFTR-HS SEKR1203AFR-HS SEKR1203AFN-76 SEKR1203AF-N-42
SEEN1203AFTN			SEE42TN-C9	SEEN1203AFTN1		SEEN42MT	SEEN1203AFTNCR-14	
SEKN1203AFTN			SEK42TN-C9	SEKN1203AFTN1 (SENN1203AFTN1)	SEKN1203AZ (SENN1203AZ)	SEKN42MT (SENN1203AFTN)	SEKN1203AFTN SEKN1203AFTN-16 SEKN42AFTN SEKN42AFTN16	
SEKN1203AFFN	K	Cast Iron	SEK42FN-C9	(SEEN1203AFFN1)	SEKN1203AZ (SENN1203AZ)	SEKN42M (SENN1203AFEN)	SEKN1203AFFN SEKN42AFFN	
SEEN1203AFFN	E	Non-ferrous metals	SEE42FN-C9	(SECN1203AFFR1)				
SEKN1203EFTR	K	Steel	SEK42TR-G3	SEKN1203EFTR1	(SECN1203EER)		SEKN1203EFTR (SECN1203EFTR) (SEEN1203EFTR) (SECN42EFTRCR) (SEEN42EFTRCR)	
SEKN1504AFTN	K	Steel	SEK53TN-C9		SEKN1504AZ	SEKN53MT		SEKN1504AFTN
SPEN1203EESR	E	Cast iron	(SPK42FR-A3E)	SPEN42EFSR1 SPEN1203EESR1 SPEN1203EEER1 (SPNN1203EEER1)				
SPMR1203EDER-H SPKR1203EDER-S	M K	Steel		(SPER1203EDER-JS)	SPKN1203EDR-WH		SPKR1203EDSR-MJ SPKR42SSR-MJ	SPKR1203EDR-76 SPKR1203EDTR-HS
SPCN1203EDTR				(SPEN1203EDR)	(SPAN1203EDR)	SPCH42TR-R	SPCN1203EDTR SPCN42STR	
SPKN1203EDTR			SPK42TR-A3	SPKN1203EDR	SPKN1203EDR	(SPCH42TR) (SPCH42TR-R)	SPKN1203EDTR SPKN42STR (SPEN1203EDTR) (SPEN42STR)	SPKN1203EDTR SPKN1203EDTR-42
SPKN1203EDFR	K	Cast iron	SPK42FR-A3		SPKN1203EDR	(SPCH42R)	SPKN1203EDFR SPKN42SFR	SPKN1203EDFR
SPKN1504EDTR	K	Steel	SPK53TR-A3	SPKN1504EDR	SPKN1504EDR	(SPCH53TR-R)	SPKN1504EDTR SPKN53STR (SPCN1504EDTR) (SPCN53STR)	SPKN1504EDTR
SPKN1504EDFR	K	Cast iron	SPK53FR-A3			(SPCH53R-R) (SPCH53TR-R)	SPKN1504EDFR SPKN53SFR	SPKN1504EDFR

Note 1. Tolerance class is different for description in ().

2. Since edge shape of milling insert is slightly different by each maker, please adjust edges (Z-axis direction) during operation.

R



Technical information

Milling insert description cross reference table

Milling insert description cross reference table

This table is Kyocera's own estimation based on publications and is not authorized by companies mentioned in it.

Kyocera	Class	Applications	MOLDINO (Mitsubishi Hitachi Tool)	Mitsubishi	Sandvik	Sumitomo	Tungaloy	Iscar
SPCN1203XPTR	C	Steel	SPC42TR-A5				SPCN1203ZPTR SPCN42ZTR	
SPKN1203XPTR	K		SPK42TR-A5				SPKN1203ZPTR SPKN42ZTR (SPEN1203ZPTR) (SPEN42ZTR)	
SPKN1203XPFR	K	Cast iron	SPK42FR-A5				SPKN1203ZPFR SPKN42ZFR	
SPKN1504XETR	K	Steel		SPK53C2SR				
TPMR1603PDER-H	M	Steel		(TPER1603PPER-JS)	(TPKN1603PPR-WH)			(TPKR1603PPTR-HS)
TPKN1603PDTR	K		TPK32TR-E0 TPK32TR-G0	TPKN1603PPR (TPEN1603PPR)	TPKN1603PPR	TPKN32TR		TPKN1603PPTR
TPKN1603PDFR	K	Cast iron	TPK32FR-E0		TPKN1603PPR	TPKN32R		TPKN1603PPFR
TPMR2204PDER-H TPKR2204PDER-S	M K	Steel		(TPER2204PDER-JS)	TPKN2204PDR-WH		TPMR2204PDSR-MJ TPKR2204PDSR-MJ TPKR43ZSR-MJ	TPKR2204PDTR-HS TPKR2204PD-R-76
TPKN2204PDTR	K		TPK43TR-E0 TPK43TR-G0	TPKN2204PDR (TPEN2204PDR)	TPKN2204PDR	(TPCH43TR)	TPKN2204PPTR TPKN43ZTR (TPCN2204PPTR) (TPCN43ZTR)	TPKN2204PDTR TPKN2204PDTR-42
TPKN2204PDFR	K	Cast iron	TPK43FR-E0			(TPCH43R)	TPKN2204PPFR TPKN43ZFR (TPCN2204PPFR) (TPCN43ZFR) (TPEN2204PTFR-16) (TPEN43ZTR)	TPKN2204PDFR
TEMR1603PTER-H	M	Steel		(TEER1603PEER-JS)			(TEKR1603PEPR-MS)	
TEKN1603PTTR	K		TEK32TR-G0 (TEE32TR-G0)	(TEEN1603PETR1)		TEKN32TR	(TECN1603PETR) (TEEN1603PETR) (TECN32ZTR) (TEEN32ZTR)	
TEKN1603PTFR	K	Cast iron	TEK32FR-G0 (TEE32FR-G0)	(TEEN1603PEFR1)		TEKN32R	(TEEN1603PEFR) (TEEN32ZFR)	
TEEN1603PTFR	E	Non-ferrous metals		(TECN1603PEFR1)		TEEN32R	(TECN1603PEFR-D) (TECN32ZFR-DIA)	
TEMR2204PTER-H TEKR2204PTER-S	M K	Steel		(TEER2204PEER-JS)			TEKR2204PEPR-MS	
TEEN2204PTTR	E		TEE43TR-GOE (TEK43TR-GOE)	TEEN2204PETR1		TEEN43TR	TEEN2204PETR (TECN2204PETR) TEEN43ZTR (TECN43ZTR)	
TEKN2204PTTR	K		TEK43TR-GOE	TEKN2204PETR1		TEKN43TR	(TEEN2204PETR) (TECN2204PETR) (TEEN43ZTR) (TECN43ZTR)	
TEKN2204PTFR	K	Cast iron	TEK43FR-GOE	(TEEN2204PEFR1)		TEKN43R	(TEEN2204PEFR) (TEEN43ZFR)	
		Non-ferrous metals		(TECN2204PEFR1)		(TEEN43R)	(TECN2204PEFR-D) (TECN43ZFR-DIA)	
SNCN1204XNTN	C	Steel	SNC43TN-D5	SNC43B2S		(CSN43MT)	SNCN1204ZNTN SNCN43ZTN	
SNKN1204XNTN	K		SNK43TN-D5	SNK43B2S		(CSN43MT)	SNKN1204ZNTN SNKN43ZTN	
SNMF1204XNTN	M	Steel	(SNKF43TN-D5)	(SNKF43B2S)		(CSNB43MT)	(SNKF1204ZNTN) (SNKF43ZFN)	

Note 1. Tolerance class is different for description in ().

2. Since edge shape of milling insert is slightly different by each maker, please adjust edges (Z-axis direction) during operation.


R



Technical information

R29

Terms and angles of turning toolholder



Function of tool angle

Tool angle	Name	Function	Effect
Rake angle	Side rake angle	· Affects cutting force, cutting heat, chip evacuation and tool life.	<ul style="list-style-type: none"> If it is positive (+) angle, sharper cutting performance is obtained. (less cutting force, less edge strength) Positive (+) angle is recommended for easy to machine workpieces or thin workpieces. Smaller rake angle or negative (-) angle is recommended when a stronger edge is required like scale machining or interrupted machining.
	Inclination angle		
Relief angle	Front relief angle Side relief angle	· Prevents the tool's contact to the workpiece surface, except the cutting edge.	<ul style="list-style-type: none"> When it is small, the cutting edge becomes strong, but the wear at relief faces may shorten the tool life.
Cutting edge angle	Cutting edge angle	· Affects chip control and the direction of cutting force.	<ul style="list-style-type: none"> When it is large, chip thickness becomes thick and chip control improves.
	Approach angle	· Affects chip control and the direction of cutting force.	<ul style="list-style-type: none"> When it is large, chip thickness becomes thin and chip control worsens, but cutting force is dispersed and edge strength improves. When it is small, chip control ability improves.
	Minor cutting edge angle	· Prevents friction between cutting edge and workpiece surface.	<ul style="list-style-type: none"> When it is large, edge strength deteriorates.

Toolholder rigidity

1. Flexure of toolholder



$$\delta = \frac{4 \times F \times (LPR)^3}{E \times B \times H^3} = \frac{4 \times k \times ap \times f \times (LPR)^3}{E \times B \times H^3}$$

Incorrect

The flexural strength of toolholder will decrease by increasing of shank height by third root and will decrease of reducing overhang by third root. Minimizing toolholder shank overhang as much as possible is important as well as shank's sectional square measure.


2. Flexure of boring bar

Symbol	Name	Unit
δ (Delta)	Deflection	mm
B	Shank width	mm
H	Shank height	mm
E	Young ratio	N/mm ²
ap	Depth of cut	mm
f	Feed rate	mm/rev
k	Specific cutting force	N/mm ³
LPR	Overhang	mm
F	Cutting force	N



(F = k × ap × f)

$$\delta = \frac{64 \times F \times (LPR)^3}{3 \times E \times \pi \times (DCON)^4} = \frac{64 \times k \times ap \times f \times (LPR)^3}{3 \times E \times \pi \times (DCON)^4}$$

Symbol	Name	Unit
δ (Delta)	Deflection	mm
DCON	Shank dia.	mm
E	Young ratio	N/mm ²
ap	Depth of cut	mm
f	Feed rate	mm/rev
k	Specific cutting force	N/mm ³
LPR	Overhang	mm
F	Cutting force	N



Terms and angles of milling cutter



Function of tool angle

Symbol	Name	Function	Effect
A	Axial rake angle (A.R.)	Controls chip flow direction and cutting force	When it is positive ... Good cutting performance and less chip welding
R	Radial rake angle (R.R.)	Controls chip flow direction and cutting force	When it is negative ... Good chip evacuation
C	Approach angle	Controls chip thickness and chip flow direction	When it is large ... Thinner chip thickness Lower cutting load
T	True rake angle	Actual rake angle	When it is positive ... Good cutting performance and less chip welding, but lower edge strength When it is negative ... Higher edge strength but easier to weld
I	Inclination angle	Controls chip flow direction	When it is positive ... Good chip evacuation Less cutting force Lower edge stability of the corner part


The formula for true rake angle: $\tan T = \tan R \times \cos C + \tan A \times \sin C$

The formula for inclination angle: $\tan I = \tan A \times \cos C - \tan R \times \sin C$

No. of Inserts (Z)

1) If the number of stages is one


If the number of stages is one, it is not indicated on the catalogue.
Please use "No. of inserts" of the catalogue for "Z" of the formula to calculate cutting conditions.



$$f_z = \frac{V_f}{Z \times n} \quad \Rightarrow \quad V_f = f_z \times Z \times n$$

2) If the number of stages is more than two

If the number of stages is more than two, it is indicated on the catalogue.
Please use "No. of flutes" of the catalogue for "Z" of the formula to calculate cutting conditions.



$$f_z = \frac{V_f}{Z \times n} \quad \Rightarrow \quad V_f = f_z \times Z \times n$$

R




Technical information


R31

Terms of solid end mill


Square



Ball-nose




Cutting edge profile




* The illustration shows squared 4 flutes tool
Core diameter rate (%) = Core diameter ÷ Outside dia. x 100

Radius




Cutting edge shape




Cutting edge with corner land

Advanced fracture resistance with corner land

General



With corner land





Trouble shooting of solid end mill

Trouble	Check item	Cutting conditions			Tool geometry			Setting	Machine
		Vc	fz	ap	Cutting direction	Low pick feed	Compressed air		
Trouble item	Higher (larger) ↑ Lower (smaller) ↓								
Edge damage	Cutting edge wear	● ↓					●		
	Unsuitable cutting conditions	● ↓						● ↑	
	Less number of blades								
Chipping of cutting edge	Up cut				Down-cut				
	Unsuitable cutting conditions	● ↓	● ↓						
	Lack of cutting edge strength							●	
Fracture occurs	Insufficient clamping force								
	Unsuitable cutting conditions	● ↓							
	Lack of tool rigidity							● ↑	●
Poor finished surface on walls	Chip packing					●		●	
	Unsuitable cutting conditions	● ↓	● ↓						
	Chip jamming								
Poor finished surface on faces	Cutting edge wear	● ↓					●		
	Large pick feed					●			
	Unsuitable cutting conditions	● ↓	● ↓						
Cutting accuracy	Out of vertical	● ↓						● ↑	● ↑
	Lack of tool rigidity							● ↑	● ↑
	Cutting edge wear	● ↓							
Poor dimensional accuracy	Unsuitable cutting conditions	● ↓	● ↓	● ↓					
	Insufficient clamping force								
	Unsuitable cutting conditions	● ↓	● ↓						
Others	Heavy chattering, vibration							● ↑	● ↑
	Lack of tool rigidity							● ↑	● ↑
	Insufficient clamping force								
Heavy chattering, vibration	Unsuitable cutting conditions	● ↓	● ↓						
	Lack of tool rigidity								
Chip jamming	Unsuitable cutting conditions	● ↓	● ↓					● ↓	
	Improper tool geometry							●	



Terms of solid drill



Trouble shooting of solid drill

Check item	Cutting conditions				Tool geometry			Setting		Machine
	Vc	fz	Lower feed at initial cutting	Lower feed when breaking through	Step feed	Coolant	Horn width	Core diameter	Shorten flute length	
Trouble	Trouble item	Higher (larger)↑ Lower (smaller)↓				Increase volume Increase pressure		Larger ↑ more Smaller ↓ less		
Edge damage	Fracture occurs	Unsuitable cutting conditions	● ↓					● ↑	●	
		Poor rigidity of drill								●
		Sloping machine face								
Chipping on peripheral cutting edge	Large peripheral cutting edge and margin land wear	Unsuitable cutting conditions	● ↓						●	
		High cutting heat at the cutting edge point				●			●	
		Poor run-out accuracy							●	
Chipping on chisel	Chipping on peripheral cutting edge	Unsuitable cutting conditions	● ↓		●			● ↓		
		Large deflection of tool holder							●	
		Chattering occurs (vibration)					● ↓			● ●
Cutting accuracy	Too wide chisel width				● ↓					
	Poor entry		●				● ↓			
	Chattering occurs (vibration)						● ↓			● ●
Burr	Enlarge hole diameter	Unsuitable cutting conditions	● ↑							
	Reduce hole diameter	Unsuitable cutting conditions	● ↓					● ↑	●	
	Poor straightness	High cutting heat at cutting edge point				●		● ↑	●	
Chip control	Poor hole position accuracy, roundness, straightness, surface roughness	Poor rigidity of drill					● ↑	●		
		Large deflection of tool holder						● ↑	●	
		Insufficient clamping force						● ↑	●	
Long chips	Large burrs at hole exit	Unsuitable cutting conditions			●			● ↓		
		Improper tool geometry							●	
		Unsuitable cutting conditions	● ↑							
Chip packing	Poor chip disposal					● ●		● ↓	●	
		Unsuitable cutting conditions	● ↓	● ↓						
		Poor chip disposal			● ●				●	

R



Technical information


Precautions when using Wiper inserts

About wiper inserts

A wiper insert is designed with a wiper edge that is located between corner radius and straight cutting edge shown as right figure.


Advantages

- A wiper edge geometry provides improved surface finish quality even at increased feed rate
- Improved machining efficiency : Reduced cutting time with higher feed rate as well as consolidation of roughing and finishing provide high machining efficiency
- Longer tool life : Reduced cutting time with higher feed rate leads to increase part production
- Excellent chip control : Higher feed rate makes chips thicker, which provides easier-to-break chips



Precautions when using WF / WE chipbreaker (negative insert)

Tip of corner-R (DNMX, TNMX)




Cautions when machining inside corner-R

Do not use this wiper insert if a precise inside corner-R is required when such a machining in the figure below.

R


Technical information



* From external turning to up facing without arc complement
(A wiper edge does not work during up facing)


DNMX / TNMX WF chipbreaker

- More incomplete cutting and excessive cutting during machining with this chipbreaker than the machining with a standard insert
- The inside corner-R dimension become smaller than the requirement.



CNMG / WNMG WF / WE chipbreaker

- The inside corner-R dimension would be smaller than the requirement (Cutting excessively).



Precautions when using Wiper inserts


WF / WE chipbreaker edge position offset adjustment

WF / WE chipbreaker (Negative Insert) edge position offset adjustment

For D type and T type, cutting edge offsets are required.

Cutting edge offsets (mm)					
DNMX150404WF DNMX150604WF		DNMX150408WF DNMX150608WF		DNMX150412WF DNMX150612WF	
X-axis direction	Z-axis direction	X-axis direction	Z-axis direction	X-axis direction	Z-axis direction
0.24	0.02	0.14	0.01	0.11	0.01

Cutting edge offsets (mm)					
TNMX160404WF		TNMX160408WF		TNMX160412WF	
X-axis direction	Z-axis direction	X-axis direction	Z-axis direction	X-axis direction	Z-axis direction
0.24	0.01	0.16	0.00	0.11	0.00




For D type and T type inserts, program corrections are required for ramping and up facing.

Program corrections for tapered part of workpiece (Z-axis direction cutting edge offsets)

DNMX1504 / DNMX1506 type

Corner-R(RE) (mm)	Ramping angle θ					
	0°	5°	10°	15°	20°	25°
0.4	0.00	-0.34	-0.35	-0.36	-0.36	-0.36
0.8	0.00	-0.26	-0.26	-0.25	-0.24	-0.22
1.2	0.00	-0.15	-0.17	-0.16	-0.15	-0.15



Corner-R(RE) (mm)	Up facing angle θ																		
	0°	5°	10°	15°	20°	25°	30°	35°	40°	45°	50°	55°	60°	65°	70°	75°	80°	85°	90°
0.4	0.00	-0.02	-0.03	-0.03	-0.04	-0.05	-0.06	-0.07	-0.08	-0.09	-0.10	-0.11	-0.12	-0.10	-0.08	-0.06	-0.04	-0.02	0.00
0.8	0.00	0.13	0.12	0.11	0.09	0.07	0.05	0.04	0.02	0.00	-0.02	-0.05	-0.07	-0.06	-0.04	-0.02	-0.01	-0.01	0.00
1.2	0.00	0.36	0.34	0.31	0.27	0.24	0.20	0.16	0.13	0.09	0.05	0.00	-0.04	-0.04	-0.02	-0.01	-0.01	-0.01	0.00


TNMX1604 type

Corner-R(RE) (mm)	Ramping angle θ					
	0°	5°	10°	15°	20°	25°
0.4	0.00					
0.8	0.00					
1.2	0.00					

Do not use TNMX1604 type insert for ramping.

Corner-R(RE) (mm)	Up facing angle θ																		
	0°	5°	10°	15°	20°	25°	30°	35°	40°	45°	50°	55°	60°	65°	70°	75°	80°	85°	90°
0.4	0.00	-0.06	-0.05	-0.05	-0.06	-0.07	-0.08	-0.08	-0.09	-0.10	-0.11	-0.12	-0.13	-0.12	-0.10	-0.07	-0.05	-0.02	0.00
0.8	0.00	0.11	0.11	0.10	0.08	0.06	0.04	0.02	0.00	-0.02	-0.04	-0.06	-0.08	-0.08	-0.06	-0.04	-0.02	-0.01	0.00
1.2	0.00	0.34	0.32	0.29	0.25	0.22	0.19	0.15	0.14	0.08	0.04	0.00	-0.05	-0.05	-0.03	-0.01	0.00	0.00	0.00

Caution (Finished edge line)



Applications	Notes
External / Facing	Toolholders for D type and T type would not be able to provide sufficient performance depending on a toolholder. Please use an applicable toolholder.
Up facing Ramping	For D type and T type inserts, program corrections on Z-axis direction are required.
Convexed-R / Concaved-R	Do not use wiper insert if a precise R shape is needed.



Technical information


R35

Precautions when using Wiper inserts

Precautions when using WP chipbreaker (Positive insert)

Proper use for a neutral insert and a handed insert


Neutral



When use a neutral type insert,

- you need to correct programs for three areas.
- it should be used for machining which does not require inside corner-R accuracy.

Handed (Left-hand shown)




When use a handed insert,

- you need to correct program for ramping.
- it provides accurate inside corner-R machining.

Less program correction is required as well as easy-to-use like a standard insert

* Position of cutting edge differs from a standard insert.
Cutting edge adjustment is required.

Caution (Finished edge line)



Neutral

Applications	Caution
Boring / Facing	Toolholders for D type and T type would not be able to provide sufficient performance depending on a toolholder. Please use an applicable toolholder.
Up Facing / Ramping	For D type and T type inserts, program corrections on Z-axis direction are required.
Convexed-R / Concaved-R	Do not use wiper inserts if a precise R shape is needed.

Handed

Applications	Caution
Boring	Toolholders for D type and TP type would not be able to provide sufficient performance depending on a toolholder. Please use an applicable toolholder.
Ramping	For D type and TP type inserts, program corrections on Z-axis direction are required.
Convexed-R / Concaved-R	Surface finish quality is as standard insert is.
Up Facing	Surface finish quality is as standard insert is.
Facing	Surface finish quality is as standard insert is.


R

Cautions when machining inside corner-R

Do not use this wiper insert if a precise inside corner-R is required when such a machining in the figure below.



Technical information




DCMX / TC(P)MX * Neutral
WP chipbreaker

- More incomplete cutting and excessive cutting during machining with this chipbreaker than the machining with a standard insert
- The inside corner-R dimension become smaller

CCMT * Neutral
DCMX / TPMX * Handed
WP chipbreaker

- No problem in the finished line on workpiece
(Adjustments are required)




R36

Precautions when using Wiper inserts


WP chipbreaker (Positive insert) Edge position offset adjustment

Neutral

For D type and T type, cutting edge offsets are required.




For D type and T type inserts, program corrections are required for ramping and up facing.




Handed

For D type and T type, cutting edge offsets are required.



For D type and T type inserts, program corrections are required for ramping.



R



Technical information

Cutting edges figuration and countermeasures

Typical cutting edge figuration		Observation	Causes	Countermeasures
Nose wear		<ul style="list-style-type: none"> Deterioration of surface roughness and dimensional accuracy 	<ul style="list-style-type: none"> Too high Vc End of tool life 	<ul style="list-style-type: none"> Reduce Vc Change to higher wear resistant grade
Notching		<ul style="list-style-type: none"> Burr formation Cutting force increase 	<ul style="list-style-type: none"> Too high f and Vc 	<ul style="list-style-type: none"> Sharper cutting performance Reduce Vc Change to higher heat resistant grade
Crater wear		<ul style="list-style-type: none"> Chip control deterioration Surface finish deterioration (peeled surface) 	<ul style="list-style-type: none"> Too high Vc 	<ul style="list-style-type: none"> Reduce Vc Change to high speed type like Cermet or Al2O3 coated insert grade
Plastic deformation		<ul style="list-style-type: none"> Workpiece dimension changes Crack at nose 	<ul style="list-style-type: none"> Too high cutting load Inappropriate insert grade 	<ul style="list-style-type: none"> Change to harder grade Reduce f and ap
Crack from wear		<ul style="list-style-type: none"> Surface finish's sudden deterioration Workpiece dimension changes 	<ul style="list-style-type: none"> Too high Vc 	<ul style="list-style-type: none"> Change the tool earlier Change to higher wear resistant grade
Chipping		<ul style="list-style-type: none"> Cutting force increase Surface roughness deterioration 	<ul style="list-style-type: none"> Too high f Chattering Lack of insert toughness 	<ul style="list-style-type: none"> Reduce f and ap Change to more rigid toolholder Change to tougher grade
Crack from welding or built-up edge		<ul style="list-style-type: none"> Surface finish deterioration Cutting force increase 	<ul style="list-style-type: none"> Too low Vc 	<ul style="list-style-type: none"> Increase Vc Improve sharp cutting performance (rake angle, chamfer)
Mechanical fracture		<ul style="list-style-type: none"> Sudden cracking Unstable tool life 	<ul style="list-style-type: none"> Too high f and ap Chattering 	<ul style="list-style-type: none"> Change to tougher grade Enlarge chamfer Enlarge Corner-R(RE) Change to more rigid toolholder
Fracture from thermal crack		<ul style="list-style-type: none"> Cracking by heat cycle Possible in interrupted machining and milling 	<ul style="list-style-type: none"> Too high Vc and f 	<ul style="list-style-type: none"> Reduce f Reduce Vc Change to dry cutting
Flaking		<ul style="list-style-type: none"> Possible in hard materials machining Possible in machining with chattering 	<ul style="list-style-type: none"> Lack of insert toughness Poor rigidity of toolholder 	<ul style="list-style-type: none"> Change to tougher grade (TiC-base ceramic to CBN.) Change to more rigid toolholder Change edge preparation

R



Technical information

Trouble shooting

Turning

Check item		Insert grades			Cutting conditions			Tool geometry			Setting	Machine									
Trouble	Countermeasures	Change to harder grade		Change to tougher grade		Change to more thermal shock resistant grade		Coolant		Chipbreaker review	Rake angle	Corner R(Rc)	Approach angle	Edge strength / Honing	Larger ↑ Smaller ↓	Change to higher tolerance (M→G)	Toolholder rigidity	Workpiece / Tool installation	Overhang length	Power, rigidity	
		Higher (Larger) ↑ Lower (Smaller) ↓	Vc	f	ap	Tool path review	Wet	Dry													
Unstable workpiece dimension	Unstable dimension	Unsuitable insert tolerance														●					
		Tool and workpiece evacuation									●	●↑	●↓	●↓				●	●	●	●
Poor surface roughness	Frequent offset during machining	Flank wear increase	●													●↑					
		Unsuitable cutting conditions				●↓	●↑														
		Built-up edge			●	●↑															
	Deterioration of accuracy or tool life by cutting heat	Poor cutting by tool wear	●		●	●↓			●		●	●↑	●↑			●↓	●				
		Chipping		●			●↓	●↓			●		●↑			●↑			●	●	●
		Welding, built-up edge			●	●↑			●		●	●↑				●↓	●				
		Unsuitable cutting conditions			●↑	●↓	●↓		●												
		Unsuitable tool geometry									●		●↑			●↓	●				
	Burr	Vibration, chattering		●		●↓	*1	●↓				●	●↑	●↓	●↓	●↓		●	●	●	●
		Unsuitable cutting conditions			●↓	●↓	●↓		●												
Edge damage	Workpiece chip off and scuffing	Unsuitable insert grades and tool geometry	●								●	●↑				●↓					
		Unsuitable cutting conditions			●↓	●↑		●	●												
	Workpiece chip off	Unsuitable insert grades and tool geometry	●						●							●	●↑	●↓	●↓	●↓	
		Unsuitable cutting conditions				●↓	●↓	●													
	Scuffing	Unsuitable cutting conditions				●↑	*2			●											
		Unsuitable insert grades and tool geometry	●				●				●	●↑				●↓					
	Wear increase at relief face, rake face	Flank wear	●			●↓			●							●↓					
		Rake face wear	●			●↓	●↓	●↓	●		●	●↑	●↑			●↑					
	Notching	Notching			●	●↓			●												
	Chipping	Vibration, chattering		●		●↓	●↓									●↑	●↑		●	●	●
	Crack	Unsuitable insert grades and cutting conditions		●	●		●↓	●↓								●↑	●↑	●↑	●	●	●
Chip control	Thermal crack	Work hardness, unsuitable insert grades and cutting conditions			●		●↓	●↓	●↓			●	●	●↑			●↓				
		Edge nose deformation during interrupted machining	●			●↓	●↓	●↓				●	●↓	●↑	●↑	●↑	●↑	●↑			
	Built-up edge	Work hardness, unsuitable insert grades and cutting conditions			●	●↑	●↑			●		●	●↑			●↓	●				
		Unsuitable cutting conditions				●↓	●↓			●											
Chips scattering	Long, tangling chips	Unsuitable cutting conditions				*3	●↓	●↑	●↑	●		●									
		Unsuitable tool geometry										●				●↓	●↓				
	Chips scattering	Unsuitable cutting conditions				●↓	●↓			●											
		Unsuitable tool geometry																			

*1. To prevent chattering, the higher f may be suitable.

*2. To prevent scuffing, the higher f may be suitable.

*3. When using X chipbreaker insert for soft steel and low carbon steel, the higher Vc cuts chips short.

R



Technical information

R39

Trouble shooting

Milling

Check item		Insert grades		Cutting conditions			Tool geometry			Setting	Machine								
Trouble	Countermeasures	Change to harder grade	Change to tougher grade	Vc	fz	ap	Coolant	Insert with chipbreaker	Relief angle	Comerangle	Edge strength / Honing	No. of inserts	Chip pocket	Wiper edge (Relief angle) / review	Insert turnout check	Cutter rigidity	Workpiece / Tool installation	Overhang length	Power, rigidity
		Change to more thermal shock resistant grade	Change to more welding resistant grade																
Edge damage	Flank wear increase	Unsuitable cutting conditions		●↓				●											
		Unsuitable tool geometry	●								●↑	●↓				●			
	Rake face wear increase	Unsuitable cutting conditions		●↓	●↓	●↓		●											
		Unsuitable tool geometry	●								●↑	●↑	●↓						
	Chipping, cracking	Unsuitable cutting conditions			●↓	●↓	●●												
		Unsuitable tool geometry	●								●↓	●↑	●↑			●	●	●	
	Edge breakage by thermal shock	Unsuitable cutting conditions		●↓	●↓	●↓				●									
		Unsuitable tool geometry	●								●↑	●↓							
	Built-up edge	Unsuitable cutting conditions		●↑	●↑			●											
		Unsuitable tool geometry	●								●↑	●↓							
Cutting accuracy	Poor surface finish	Unsuitable cutting conditions		●↑	●↓	●↓		●											
		Unsuitable tool geometry	●		●								●↓	●↓	●	●	●	●	
	Burr formation	Unsuitable cutting conditions		●↓	●↓	●↓	●●						●↑	●↓	●↓				
		Unsuitable tool geometry														●			
	Workpiece chip off	Unsuitable cutting conditions		●↓	●↓		●												
		Unsuitable tool geometry									●↑	●↑	●↓	●↑		●			
Others	Poor planeness / parallelism	Tool and workpiece evacuation		●↓	●↓			*5		●●	●●	●●	●●	●●	●●	●●	●●	●●	
	Heavy chattering, vibration	Unsuitable cutting conditions, installation		●↓	*1 ●↓	*2 ●↓	●●	*4		●●	●●	●●	●●	●●	●●	●●	●●	●●	
	Chip jamming	Unsuitable cutting conditions		●↑	*3 ●↓		●●	*6	●●										
		Unsuitable tool geometry								●●	●●								

*1. To prevent chattering, the higher fz may be suitable.

*2. To prevent chattering, the larger ap may be suitable.

*3. Higher fz may be suitable.

*4. Down-cut method is recommended for helical end milling.

*5. If the surface is warped by cutting heat.

*6. Compressed air is recommended.



Technical information

Trouble shooting

Drilling (MagicDrill series)

Check item		Insert grades		Cutting conditions		Tool geometry		Setting			Machine			
Trouble	Countermeasures	Change to harder grade	Change to tougher grade	Vc	fz	Coolant discharge condition	Chipbreaker review	Inner edge's center height check (Core dia. check)	Toolholder rigidity improvement (Short type)	Workpiece / Tool installation	Insert installation	Offset check	Adjustable sleeve usage	Power, rigidity
Edge damage	Unusual wear	Unsuitable cutting speed (too high)	●		●↓									
		Unsuitable cutting speed (too low)		●	●↑									
		Unsuitable coolant discharge				●								
		Poor rigidity of machine / workpiece								●				●
		Small hole dia.										*1	●	●
		Unsuitable insert grade	●											
Outer edge cracking	Inner edge cracking	No core, too small core						●↑						
		Poor rigidity of machine / workpiece							●	●				●
		Unstable drilling start			●↓									
		High hardness workpiece	●		●↓	●↓								
		Clogged chips		●↑				●↓						
		Unstable insert installation								●				
Toolholder, others	Scratches on tool body	Poor rigidity of machine / workpiece									●			●
		Inaccurate tool installment										*1	●	●
		Clogged chips		●↑	●↓									
		Unstable drilling start			●↓									
		Poor rigidity of machine / workpiece								●				●
		Poor rigidity of toolholder							●		●			
Poor hole dia. accuracy / Surface finish	Large vibration / chattering	Inaccurate tool installment										*1	●	●
		Clogged chips		●↑	●↓			●↓						
		Large core dia.						●↓						
		Unstable drilling start			●↓									
		Unsuitable coolant discharge				●								
		Unsuitable cutting conditions, installation		●↑	●↓					●	●			●
Long chips	Machine failure	Unsuitable cutting conditions		●↑										
		Unsuitable chipbreaker						●						
		Lack of machine power		●↓	●↓			●						●

*1. For lathe operation

R



Technical information

Basic formulas

Turning


Cutting speed

$$V_c = \frac{\pi \times D_m \times n}{1,000}$$

V_c : Cutting speed [m/min]

D_m : Workpiece dia. [mm]

n : Spindle revolution [min^{-1}]



Power requirement

$$P_c = \frac{K_s \times V_c \times a_p \times f}{6,120 \times \eta}$$

P_c : Power requirement [kW]

P_{HP} : Power requirement (Horse power) [HP]

$$P_{HP} = \frac{K_s \times V_c \times a_p \times f}{4,500 \times \eta}$$

V_c : Cutting speed [m/min]

a_p : Depth of cut [mm]

f : Feed rate [mm/rev]

K_s : Specific cutting force [kgf/mm²]

η : Mechanical efficiency (0.7 ~ 0.8)

K_s [kgf/mm ²]	
Low carbon steel	190
Medium carbon steel	210
High carbon steel	240
Low alloy steel	190
High alloy steel	245
Cast iron	93
Malleable cast iron	120
Bronze, brass	70


Theoretical surface roughness

$$Rz(h) = \frac{f^2}{8 \times RE} \times 1,000$$

$Rz(h)$: Theoretical surface roughness [μm]

f : Feed rate [mm/rev]

RE : Corner radius of insert [mm]



Chip removal volume

$$Q = V_c \times a_p \times f$$

Q : Chip removal volume [$\text{cm}^3/\text{min}=\text{cc}/\text{min}$]

V_c : Cutting speed [m/min]


a_p : Depth of cut [mm]

f : Feed rate [mm/rev]

Edge position compensation when changing corner-R(RE)

$$\Delta X = (RE - RE') \times \left\{ \frac{\cos \left(\frac{EPSR}{2} + (KRINS - 90^\circ) \right)}{\sin \frac{EPSR}{2}} - 1 \right\}$$

$$\Delta Z = (RE - RE') \times \left\{ \frac{\sin \left(\frac{EPSR}{2} + (KRINS - 90^\circ) \right)}{\sin \frac{EPSR}{2}} - 1 \right\}$$



ΔX : X-axis direction cutting edge offsets [mm]

ΔZ : Z-axis direction cutting edge offsets [mm]

RE : Corner-R before change [mm]

RE' : Corner-R after change [mm]

$EPSR$: Insert corner angle [°]

$KRINS$: Toolholder's cutting edge angle [°]

Toolholder type	Insert corner angle EPSR	Cutting edge angle KRINS	ΔX	ΔZ
DCLN/PCLN	80°	95°	0.100 \times (RE-RE')	0.100 \times (RE-RE')
DTGN/PTGN	60°	91°	0.714 \times (RE-RE')	0.030 \times (RE-RE')
DDJN/PDJN	55°	93°	0.866 \times (RE-RE')	0.099 \times (RE-RE')
DDHN/PDHN	55°	107.5°	0.531 \times (RE-RE')	0.531 \times (RE-RE')
DVLN/PVLN	35°	95°	2.072 \times (RE-RE')	0.273 \times (RE-RE')
DVPN/PVPN	35°	117.5°	1.351 \times (RE-RE')	1.351 \times (RE-RE')
DSBN/PSBN	90°	75°	0.225 \times (RE-RE')	-0.293 \times (RE-RE')

Example: Compensation when changing corner-R from 0.8 to 0.4, using PCLN toolholder,

$$\Delta X=0.100 \times (0.8-0.4)=0.04(\text{mm})$$

$$\Delta Z=0.100 \times (0.8-0.4)=0.04(\text{mm})$$



Basic formulas

Turning (Cutting time)

Cutting time (External turning case 1: 1 pass machining)


At constant revolution

$$T = \frac{60 \times L}{f \times n}$$

At constant cutting speed

$$T = \frac{60 \times \pi \times L \times D_m}{1,000 \times f \times V_c}$$

- T : Cutting time [sec]
 L : Cutting length [mm]
 f : Feed rate [mm/rev]
 n : Spindle revolution [min^{-1}]
 D_m : Workpiece dia. [mm]
 V_c : Cutting speed [m/min]



Cutting time (External turning case 2: multi-pass machining)


At constant revolution

$$T = \frac{60 \times L}{f \times n} \times N$$

At constant cutting speed

$$T = \frac{60 \times \pi \times L \times (D_1 + D_2)}{2 \times 1,000 \times f \times V_c} \times N$$

- T : Cutting time [sec]
 L : Cutting length per pass [mm]
 ap : Depth of cut per pass [mm]
 f : Feed rate [mm/rev]
 n : Spindle revolution [min^{-1}]
 D₁ : Max. dia. of workpiece [mm]
 D₂ : Min. dia. of workpiece [mm]
 V_c : Cutting speed [m/min]
 N : Number of passes = $(D_1 - D_2) / ap / 2$ (if it is indivisible, obtain integer by rounding up one place of decimals.)



Cutting time (Facing)


At constant revolution

$$T = \frac{60 \times (D_1 - D_2)}{2 \times f \times n} \times N$$

At constant cutting speed

$$T_1 = \frac{60 \times \pi \times (D_1 + D_2) \times (D_1 - D_2)}{4,000 \times f \times V_c} \times N$$

- T : Cutting time [sec]
 T₁ : Cutting time before reaching
 Max. spindle revolution [sec]
 L : Cutting length [mm]
 ap : Depth of cut per pass [mm]
 f : Feed rate [mm/rev]
 n : Spindle revolution [min^{-1}]
 D₁ : Max. dia. of workpiece [mm]
 D₂ : Min. dia. of workpiece [mm]
 V_c : Cutting speed [m/min]
 N : Number of passes = L / ap (if it is indivisible, obtain integer by rounding up one place of decimals.)



Cutting time (Grooving)


At constant revolution

$$T = \frac{60 \times (D_1 - D_2)}{2 \times f \times n}$$

At constant cutting speed

$$T_1 = \frac{60 \times \pi \times (D_1 + D_2) \times (D_1 - D_2)}{4,000 \times f \times V_c}$$

- T : Cutting time [sec]
 T₁ : Cutting time before reaching
 Max. spindle revolution [sec]
 L : Cutting length [mm]
 f : Feed rate [mm/rev]
 n : Spindle revolution [min^{-1}]
 D₁ : Max. dia. of workpiece [mm]
 D₂ : Min. dia. of workpiece [mm]
 V_c : Cutting speed [m/min]



R

Cutting time (Cut-off)

At constant revolution


$$T = \frac{60 \times D_1}{2 \times f \times n}$$

At constant cutting speed

$$T_1 = \frac{60 \times \pi \times (D_1 + D_3) \times (D_1 - D_3)}{4,000 \times f \times V_c}$$

$$T_3 = T_1 + \frac{60 \times D_3}{2 \times f \times n_{\max}}$$

- T : Cutting time [sec]
 T₁ : Cutting time before reaching
 Max. spindle revolution [sec]
 T₃ : Cutting time when reaching
 Max. spindle revolution [sec]
 f : Feed rate [mm/rev]
 n : Spindle revolution [min^{-1}]
 n_{max} : Max. spindle revolution [min^{-1}]
 D₁ : Max. dia. of workpiece [mm]
 D₃ : Diameter when reaching max. spindle revolution [mm]
 V_c : Cutting speed [m/min]



Technical information

R43

Basic formulas

Milling

Cutting speed

$$V_c = \frac{\pi \times DC \times n}{1,000}$$

V_c : Cutting speed [m/min]

DC : Cutter dia. [mm]

n : Spindle revolution [min^{-1}]




Table feed & feed per tooth


$$f_z = \frac{V_f}{Z \times n}$$

f_z : Feed per tooth [mm/t]

V_f : Table feed [mm/min]

Z : No. of inserts

n : Spindle revolution [min^{-1}]



Power requirement

$$P_c = \frac{K_s \times Q}{6,120 \times \eta} = \frac{K_s \times ae \times V_f \times ap}{6,120,000 \times \eta}$$

$$= \frac{K_s \times ae \times f_z \times Z \times n \times ap}{6,120,000 \times \eta}$$

$$P_{HP} = \frac{6,120}{4,500} \times P_c$$

P_c : Power requirement [kW]

P_{HP} : Power requirement (Horse power) [HP]

ae : Width of cut [mm]

V_f : Table feed [mm/min]

f_z : Feed per tooth [mm/t]

Z : No. of inserts

n : Spindle revolution [min^{-1}]

ap : Depth of cut [mm]

K_s : Specific cutting force [kgf/mm^2]

η : Mechanical efficiency (0.7 ~ 0.8)

Q : Chip removal volume [$\text{cm}^3/\text{min}=\text{cc}/\text{min}$]

$K_s [\text{kgf/mm}^2]$	
Low carbon steel	190
Medium carbon steel	210
High carbon steel	240
Low alloy steel	190
High alloy steel	245
Cast iron	93
Malleable cast iron	120
Bronze, Brass	70

Chip removal volume

$$Q = \frac{ae \times V_f \times ap}{1,000} = \frac{ae \times f_z \times Z \times n \times ap}{1,000}$$

Q : Chip removal volume [$\text{cm}^3/\text{min}=\text{cc}/\text{min}$]

ae : Width of cut [mm]

V_f : Table feed [mm/min]

f_z : Feed per tooth [mm/t]

Z : No. of inserts

n : Spindle revolution [min^{-1}]

ap : Depth of cut [mm]

R



Technical information

Cutting time

$$T = \frac{60 \times L'}{V_f} = \frac{60 \times L'}{f_z \times Z \times n}$$

T : Cutting time [sec]


L' : Total table transfer length [mm]

(= L+DC+2a)

L : Workpiece length [mm]

DC : Cutter dia. [mm]

a : Idling distance [mm]



V_f : Table feed [mm/min]

f_z : Feed per tooth [mm/t]

Z : No. of inserts

n : Spindle revolution [min^{-1}]

Basic formulas


True rake angle

$$\tan T = \tan R \cos C + \tan A \sin C$$

Inclination angle

$$\tan I = \tan A \cos C - \tan R \sin C$$

A (GAMP) : Axial rake angle (A.R.) [°] (-90° < A < 90°)
R (GAMF) : Radial rake angle (R.R.) [°] (-90° < R < 90°)
C (KAPR) : Approach angle [°] (0° < C < 90°)
T (GAMN) : True rake angle [°] (-90° < T < 90°)
I (GAMO) : Inclination angle [°] (-90° < I < 90°)



Ball-nose end mill cutting speed & revolution


$$n = \frac{1,000 \times V_a}{2 \times \pi \times \sqrt{ap(2RE-ap)}}$$

n : Revolution [min⁻¹]

RE : Radius of ball-nose end mill (Ball part's radius) [mm]

ap : Depth of cut [mm]

V_a : Cutting speed at actual dia. d [m/min]



Drilling (MagicDrill series)


Cutting speed

$$V_c = \frac{\pi \times DC \times n}{1,000}$$

V_c : Cutting speed [m/min]

DC : Drill dia. [mm]

n : Spindle revolution [min⁻¹]



Feed rate (Milling)

$$V_f = f_z \times Z \times n$$

V_f : Table feed [mm/min]

f_z : Feed per tooth [mm/t]

Z : No. of inserts (No. of insert = 1)

n : Spindle revolution [min⁻¹]

Cutting time

$$T = \frac{60 \times L}{f \times n} = \frac{60 \times \pi \times DC \times L}{1,000 \times V_c \times f}$$

T : Cutting time [sec]

L : Drilling depth [mm]

f : Feed rate [mm/rev]

n : Spindle revolution [min⁻¹]

DC : Drill dia. [mm]

V_c : Cutting speed [m/min]

R




Technical information


R45

Tooling examples of small parts machining

Tooling example1: CNC automatic lathe (Gang type)



Tooling example 2: CNC automatic lathe (Gang type)




R
Technical information


R46

Tooling examples of small parts machining

Tooling example 3: CNC automatic lathe (Opposed gang type)



Tooling example 4: CNC automatic lathe (Turret type)



For Tooling Layout and Automatic Lathe List by Manufacturer, See Page R46~R54

R



Technical information

R47

Automatic lathe list by manufacturer

Citizen machinery (Cincom Products)

Model	Toolholder dimensions (Gang tool post)	Number of tools	Toolholder dimensions (Turret tool post)	Number of tools	Sleeve dia. (Horizontal/Opposed)	Max. cutting dia.	Remarks
A12/16	10 x 10 x 100	5			ø19.05/ø20	ø12/ø16	
A20	12(13) x 12(13) x 120 * Cut-off toolholder: □16mm	6			ø25.4	ø20	
A20 VII	12(13) x 12(13) x 120 * Cut-off toolholder: □16mm	6			ø25.4	ø20	
A32	16 x 16 x 150	6			ø25.4	ø32	
B12	10 x 10 x 100	5			ø19.05/ø20	ø12	
B12E/B16E	10 x 10 x 120(60)	5			ø19.05(ø20 ^{0P})	ø12/ø16	
B20	12(13) x 12(13) x 120	6			ø19.05/ø20	ø20	
BL12	10 x 10 x 60 ~ 120	5			ø20(ø19.05)	ø12	
BL20/25	12(13) x 12(13) x 120	4 ~ 7			ø20(ø19.05)	ø20/ø25	
C12/16	10 x 10 x 120	6			ø19.05	ø12/ø16	
C32	16 x 16 x 130	5			ø25.4	ø32	
D25	16 x 16 x 150 * Cut-off toolholder: □19mm				ø25.4	ø25	
F10			10 x 10 x 60	10	ø19.05	ø10	
F12			10 x 10 x 60	10	ø19.05	ø12	
F16			10 x 10 x 60	10	ø19.05	ø16	
F20			16(19) x 16(13) x 90	10	ø25.4	ø20	
F25			16(19) x 16(13) x 90	10	ø25.4	ø25	
FL25			16 x 16 x 90	12		ø25	
FL42			16 x 16 x 90	12		ø42	
G32			16(19) x 16(19) x 90	10	-	ø32	
K12/16	12(10) x 12(10) x 100	6(7)			ø19.05/ø20	ø12/ø16	
K12E/K16E	12 x 12 x 120	6			ø19.05/ø20	ø12/ø16	
L10	8 x 8 x 100 ~ 130	5			ø15.875	ø10	
L12	10 x 10 x 100	6			ø19.05	ø12	
L16	12(10) x 12(10) x 130	5			ø19.05	ø16	
L20,L20E	12 x 12 x 130 * Cut-off toolholder: □16mm	5			ø19.05	ø20	
L20X,L220	12(13,16) x 12(13,16) x 120 * Cut-off toolholder: □16mm	5 ~ 7			ø19.05	ø20	
L25	16 x 16 x 130	5			ø25.4	ø25	
L32	16 x 16 x 130	5			ø25.4	ø32	
M12	10 x 10 x 120	5	10 x 10 x 60	10 + a	ø19.05	ø12	
M16	10 x 10 x 120	5	10 x 10 x 60	10 + a	ø19.05	ø16	
M20	16 x 16 x 130	5	16 x 16 x 90	10 + a	ø25.4	ø20	
M32	16 x 16 x 130	5	16 x 16 x 90	10 + a	ø25.4	ø32	
MC20	13 x 13 x 120	2 + 2 + 2			ø19.05/ø20.0	ø20.0	
MSL12	10 x 10 x 120				-	ø12	
R04	8 x 8 x 120	5			ø15.875	ø4	
R07	8 x 8 x 120	5			ø15.875	ø7	
RL01	10(8) x 10(8) x 90				ø16(ø20)	ø10	
RL02	16 x 16 x 90				ø20	ø20	
RL21	10(12) x 10(12) x 90				ø19.05	ø35	

Manufacturers are in no particular order.



Automatic lathe list by manufacturer

Citizen machinery (Miyano Products)

Model	Toolholder dimensions (Gang tool post)	Number of tools	Toolholder dimensions (Turret tool post)	Number of tools	Sleeve dia. (Horizontal/Opposed)	Number of tools	Max. cutting dia.	Remarks
ABX-51SY2			20 x 20 x 125(100)	24	ø25	48	ø51	
ABX-51SYY2			20 x 20 x 125(100)	24	ø25	48	ø51	
ABX-51TH5			20 x 20 x 125(100)	36	ø25	72	ø51	
ABX-51THY2			20 x 20 x 125(100)	36	ø25	72	ø51	
ABX-64SY2			20 x 20 x 125(100)	24	ø25	48	ø64	
ABX-64SYY2			20 x 20 x 125(100)	24	ø25	48	ø64	
ABX-64TH5			20 x 20 x 125(100)	36	ø25	72	ø64	
ABX-64THY2			20 x 20 x 125(100)	36	ø25	72	ø64	
BNA-34C			20 x 20 x 125(100)	8(16)	ø25	24	ø34	
BNA-34DHY			20 x 20 x 125(100)	14(22)	ø25	27	ø34	
BNA-34S			20 x 20 x 125(100)	8(16)	ø25	24	ø34	
BNA-42C/C2			20 x 20 x 125(100)	8(16)	ø25	24	ø42	
BNA-42DHY			20 x 20 x 125(100)	14(22)	ø25	27	ø42	
BNA-42DHY2			20 x 20 x 125(100)	14(22)	ø25	27	ø42	
BNA-42DHY3			20 x 20 x 125(100)	14(22)	ø25	27	ø42	
BNA-42GTY	20 x 20 x 125(100)	3	20 x 20 x 125(100)	8(16)	ø25	24(7)	ø42	
BNA-42MSY2			20 x 20 x 125(100)	8(16)	ø25	24	ø42	
BNA-42S/S2			20 x 20 x 125(100)	8(16)	ø25	24	ø42	
BNA-42CS/SYS			20 x 20 x 125(100)	12(24)	ø25	24	ø42	
BNC-42C7			20 x 20 x 125(100)	8(16)	ø25	24	ø42	
BND-51C2			20 x 20 x 125(100)	12	ø25	24	ø51	
BND-51S2			20 x 20 x 125(100)	12	ø25	24	ø51	
BND-51SY2			20 x 20 x 125(100)	12	ø25	24	ø51	
BNE-42S6			20 x 20 x 125(100)	24	ø25	48	ø42	
BNE-42SY6			20 x 20 x 125(100)	24	ø25	48	ø42	
BNE-51S6			20 x 20 x 125(100)	24	ø25	48	ø51	
BNE-51SY6			20 x 20 x 125(100)	24	ø25	48	ø51	
BNE-51MSY			20 x 20 x 125(100)	24	ø25	48	ø51	
BNE-51MYY			20 x 20 x 125(100)	24	ø25	48	ø51	
BNE-65MYY			20 x 20 x 125(100)	24	ø25	48	ø65	
BNJ-34S3/S5			20 x 20 x 125(100)	18	ø25	30	ø34	
BNJ-34SY3/SYS			20 x 20 x 125(100)	18	ø25	30	ø34	
BNJ-42S3/S5			20 x 20 x 125(100)	18	ø25	30	ø42	
BNJ-42S6			20 x 20 x 125(100)	20	ø25	40	ø42	
BNJ-42SY3/SYS			20 x 20 x 125(100)	18	ø25	30	ø42	
BNJ-42SY5			20 x 20 x 125(100)	18	ø25	30	ø42	
BNJ-42SY6			20 x 20 x 125(100)	20	ø25	40	ø42	
BNJ-51S3/S5			20 x 20 x 125(100)	18	ø25	30	ø51	
BNJ-51SY3/SYS			20 x 20 x 125(100)	18	ø25	30	ø51	
BNJ-51SY6			20 x 20 x 125(100)	20	ø25	40	ø51	
GN-3200	12(16) x 12(16) x 70 ~ 120	4 ~ 5			ø20		ø40	
GN-3200W	12(16) x 12(16) x 70 ~ 120	4 ~ 5			ø20		ø40	"Number of tools" is per turret.
GN-4200	12(16) x 12(16) x 70 ~ 120	6 ~ 7			ø20		ø40	
LX-06E2			20 x 20 x 125(100)	8	ø32	8		6 inch power chuck
LX-06E3			20 x 20 x 125(100)	8	ø32	8		6 inch power chuck
LX-08C			25 x 25 x 150	10	ø40	10		8 inch power chuck
LX-08E2			25 x 25 x 150	8	ø40	8		8 inch power chuck
LX-08E3			25 x 25 x 150	8	ø40	8		8 inch power chuck
LX-08R			20 x 20 x 125(100)	10	ø25	20		8 inch power chuck
LZ-01R2			20 x 20 x 125(100)	12	ø25	24		6 inch power chuck
LZ-01RY2			20 x 20 x 125(100)	12	ø25	24		6 inch power chuck
LZ-02R2			20 x 20 x 125(100)	10	ø25	20		8 inch power chuck
LZ-02RY2			20 x 20 x 125(100)	10	ø25	20		8 inch power chuck
RL01III	10 x 10 x 70 ~ 120	2 ~ 3			ø16		ø10	
RL01V	10 x 10 x 70 ~ 120	2 ~ 3			ø16		ø10	
RL03	12(16) x 12(16) x 70 ~ 120	4 ~ 5			ø20		ø40	
VC03	12(16) x 12(16) x 70 ~ 120	4 ~ 5			ø20		ø40	

* Number of tools shown in parentheses is the maximum number of toolholder mountable including ø25 sleeves.

Manufacturers are in no particular order.

R



Technical information

R49

Automatic lathe list by manufacturer

Star Micronics

Model	Toolholder dimensions (Gang tool post)	Number of tools	Toolholder dimensions (Turret tool post)	Number of tools	Sleeve dia. (Front/Rear)	Number of tools	Max. cutting dia.	Remarks
SB-16 (A/C/D/E)	12 x 12 x 95 ~ 130 12(10) x 12(10) x 95 ~ 130	5 6			ø22/ø22 ø22/ø22	4/4 4/4	ø16 ø16	Only D/E for rear-end sleeves
SB-12II (C/E)	12 x 12 x 95 ~ 130	6			ø22/ø22	4/4	ø13	
SB-16II (C/E)	12(10) x 12(10) x 95 ~ 130	6			ø22/ø22	4/4	ø16	Only E for rear-end sleeves
SB-20 A/C/E	12 x 12 x 95 ~ 130	6			ø22/ø22	4/4	ø20	
SB-12R typeG	12 x 12 x 95 ~ 130	6			ø22/ø22	4/4	ø13	
	10 x 10 x 95 ~ 130	7			ø22/ø22	4/4		
SB-16III	12 x 12 x 95 ~ 130	5			ø22/ø22	4/4	ø16	
	10 x 10 x 95 ~ 130	6			ø22/ø22	4/4		
SB-16R/20R typeN	12 x 12 x 95 ~ 130	6			ø22/ø22	4/4	ø16/ø23	
	10 x 10 x 95 ~ 130	7			ø22/ø22	4/4	ø16/ø23	
SB-16R/20R typeG	12 x 12 x 95 ~ 130	6			ø22/ø22	4/4	ø16/ø23	
	10 x 10 x 95 ~ 130	7			ø22/ø22	4/4	ø16/ø23	
SB-16R/20R typeGB	12 x 12 x 95 ~ 130	6			ø22/ø22	4/4	ø16/ø23	
	10 x 10 x 95 ~ 130	7			ø22/ø22	4/4	ø16/ø23	
SC20	12 x 12 x 95 ~ 130	5			ø22/-	4/-	ø20	
	10 x 10 x 95 ~ 130	6			ø22/-	4/-	ø20	
SG-42			16 x 16 x 84 ~ 88(71 ~ 82) 20 x 20 x 84 ~ 88		ø22+ø32/-		ø42	
SL-7/10	10 x 10 x 95 ~ 115	6			ø16+ø22/ø16+ø22	4~6/6	ø10	
	8 x 8 x 68 ~ 115	6						
SR-10J	8 x 8 x 67 ~ 110 (Spacer is needed)	6			ø16/ø16+ø22	4/4	ø10	
SR-20RII	12 x 12 x 100 ~ 135	6			ø22/ø22	4/4	ø23	
SR-20RIII	12 x 12 x 95 ~ 135	6			ø22/ø22	6/4	ø23	
SR-20J typeC	12 x 12 x 95 ~ 135	6			ø22/ø22	6/4	ø23	
SR-20J typeN	12 x 12 x 95 ~ 135	6			ø22/ø22	6/4	ø23	
SR-20JII typeA	12 x 12 x 100 ~ 135	6			ø22/ø22	7/4	ø23	
SR-20JII typeB	12 x 12 x 100 ~ 135	6			ø22/ø22	7/8	ø23	
SR-20JV typeA	12 x 12 x 100 ~ 130	7			ø22/ø22	6/8	ø23	
SR-20JV typeB	12 x 12 x 100 ~ 130	7			ø22/ø22	6/8	ø23	
SR-25J/32J	16 x 16 x 95 ~ 155	6			ø22+ø32/ø22	4/4	ø32	
SR-32JII typeA	16 x 16 x 95 ~ 165	6			ø22+ø32/ø22	5/6	ø34	
SR-32JII typeB	16 x 16 x 95 ~ 165	6			ø22+ø32/ø22	5/8	ø34	
SR-32JIII typeA	16 x 16 x 95 ~ 165	6			ø22+ø32/ø22	5/6	ø34	
SR-32JIII typeB	16 x 16 x 95 ~ 165	6			ø22+ø32/ø22	5/8	ø34	
SR-38 typeA	16 x 16 x 95 ~ 135	4						
	16 x 16 x 100	2						
	20 x 20 x 105 ~ 135 (Cut-off)	1			ø22+ø32/ø22	5/8	ø38	
SR-38 typeB	16 x 16 x 95 ~ 135	4						
	16 x 16 x 100	2			ø22+ø32/ø22	5/8	ø38	
	20 x 20 x 105 ~ 135 (Cut-off)	1						
SR-38J	16 x 16 x 95 ~ 135	4						
	16 x 16 x 95 ~ 135 (Optional)	3			ø22+ø32/ø22	5/4	ø38	
	20 x 20 x 105 ~ 135 (Cut-off)	1						
ST-20			12 x 12 x 73 ~ 79 12 x 12 x 65 ~ 73 (Cut-off) 16 x 16 x 64 ~ 73 16 x 16 x 65 ~ 73 (Cut-off)		ø22+ø32/ø22+ø32		ø20	
ST-38			16 x 16 x 83 ~ 88 16 x 16 x 71 ~ 82 16 x 16 x 84 ~ 88 (Cut-off) 20 x 20 x 84 ~ 88 20 x 20 x 84 ~ 88 (Cut-off)		ø22+ø32/ø22+ø32		ø38	
SV-12/20	12 x 12 x 95 ~ 135	5	12 x 12 x 70 ~ 78		ø22+ø32/-		ø12/ø20	
	16 x 16 x 95 ~ 135	4	16 x 16 x 65 ~ 70					
SV-20R	12 x 12 x 95 ~ 135	7	12 x 12 x 70 ~ 78		ø22+ø32/ø22	- / 8	ø23	
	16 x 16 x 95 ~ 135	6	16 x 16 x 65 ~ 70					
SV-32	16 x 16 x 95 ~ 135	4	16 x 16 x 60 ~ 78(80 ~ 88)		ø22+ø32/-		ø32	
	16 x 16 x 105 ~ 135	4	16 x 16 x 84 ~ 88					
SV-38R	20 x 20 x 115 ~ 135 (Cut-off)	1	16 x 16 x 71 ~ 82		ø22+ø32/ø34	- / 8	ø38	
			20 x 20 x 84 ~ 88					
SW-12RII	10 x 10 x 95 ~ 115	7			ø16/ø22	4/8	ø13	
SW-20	12 x 12 x 80 ~ 150	6			ø22/ø22	4/8	ø23	
	16 x 16 x 80 ~ 144							
SX-38 typeA	16 x 16 x 95 ~ 135	4	16 x 16 x 84 ~ 88		ø22+ø32/ø34	- / 8	ø38	
	20 x 20 x 105 ~ 135 (Cut-off)	1	16 x 16 x 71 ~ 82					
SX-38 typeB	16 x 16 x 95 ~ 135	4	16 x 16 x 84 ~ 88		ø22+ø32/ø34	- / 8	ø38	
	20 x 20 x 105 ~ 135 (Cut-off)	1	16 x 16 x 71 ~ 82					
			20 x 20 x 84 ~ 88					

Manufacturers are in no particular order.



Automatic lathe list by manufacturer

Eguro

Model	Toolholder dimensions (Gang tool post)	Number of tools	Toolholder dimensions (Turret tool post)	Number of tools	Sleeve dia. (Horizontal/Opposed)	Number of tools	Max. cutting dia.	Remarks
NUCBOY-8EX	12 x 12	6			ø20 or ø25 or ø30	5	ø20	
NUCLET-10EX/EL	16 x 16	6			ø20 or ø25 or ø30	5	ø25.5	
NUCPAL-10EX/EL	16 x 16	10			ø20 or ø25 or ø30	8	ø25.5	
NUCLET-10vv	16 x 16	6			ø20 or ø25 or ø30	5	ø25.5	
NUCBOY-8LL	12 x 12	2			ø20 or ø25 or ø30	2	ø20	
NUCLET-10LL	16 x 16	2			ø20 or ø25 or ø30	2	ø25.5	
NUCROBO-8EX	12 x 12	6			ø20 or ø25 or ø30	5	ø20	
NUCROBO-101	16 x 16	6			ø20 or ø25 or ø30	5	ø25.5	
NUCROBO-202	16 x 16	10			ø20 or ø25 or ø30	8	ø25.5	
SANAX-6	12 x 12	10			ø12 or ø16/ø30	3~6/2	ø15	
SANAX-10	16 x 16	10			ø20 or ø30/ø30	5~8/3	ø25.5	
SANATURN-6	12 x 12	5			ø16/ø30	3~5/2	ø15	
SANATURN-10	16 x 16	6			ø20/ø30	7/3	ø25.5	
EBN-10EX	12 x 12	5			ø20 or ø25 or ø30	4	ø25.5	
GL-120	12 x 12	4			-		ø20	
EB-6	8 x 8	2			-		ø15	
EB-8	10 x 10	2			-		ø20	
EB-10	10 x 10	2			-		ø25.5	

Manufacturers are in no particular order.

R



Technical information

R51

Automatic lathe list by manufacturer

Tsugami

Model	Toolholder dimensions (Gang tool post)	Number of tools	Toolholder dimensions (Turret tool post)	Number of tools	Sleeve dia. (Horizontal/Opposed)	Number of tools	Max. cutting dia.	Remarks
B073-III	8 x 8 x 85	9	-	-	ø20/-	4/-	ø7	
B074/075-III	8 x 8 x 85	9	-	-	ø20/ø20	4/4(8)	ø7	
B0123-III	12 x 12 x 85	9	-	-	ø20/-	4/-	ø12	
B0124/125/126-III	12 x 12 x 85	9	-	-	ø20/ø20	4/4(8)	ø12	
B0128W	12 x 12 x 85	9	-	-	ø20/ø20	4/8	ø12	
B0203-III	12 x 12 x 85	9	-	-	ø20/-	4/-	ø20	
B0204/205/206-III	12 x 12 x 85	9	-	-	ø20/ø20	4/4(8)	ø20	
B0208W	12 x 12 x 85	9	-	-	ø20/ø20	4/8	ø20	
BM163-III	12 x 12 x 85	9	-	-	ø20/-	4/-	ø16	
BM164/165-III	12 x 12 x 85	9	-	-	ø20/ø20	4/4(8)	ø16	
BW127J-I/II	12 x 12 x 85	7	-	-	ø20/ø20	3/9	ø20	
BW128J-I/II	12 x 12 x 85	7	-	-	ø20/ø20	3/9	ø20	
BW128ZJ-I/II	12 x 12 x 85	7	-	-	ø20/ø20	3/9	ø20	
BW129ZJ-I/II	12 x 12 x 85	7	-	-	ø20/ø20	3/9	ø20	
BW207J-I/II	12 x 12 x 85/16 x 16 x 85	5/2	-	-	ø20/ø20	3/9	ø20	
BW208J-I/II	12 x 12 x 85/16 x 16 x 85	5/2	-	-	ø20/ø20	3/9	ø20	
BW208ZJ-I/II	12 x 12 x 85/16 x 16 x 85	5/2	-	-	ø20/ø20	3/9	ø20	
BW209ZJ-I/II	12 x 12 x 85/16 x 16 x 85	5/2	-	-	ø20/ø20	3/9	ø20	
B0265/265B/266-II	16 x 16 x 100	12	-	-	ø25/ø25	5/4	ø26	
B0325/325B/326-II	16 x 16 x 100	12	-	-	ø25/ø25	5/4	ø32	
B0385/385L	20 x 20 x 125	8	-	-	ø32/ø32	3/5	ø38	
B0265/266-III B0266/326-III	16 x 16 x 100	12	-	-	ø25/ø25	5/4	ø26/ø32	
B0265/325V-III B0266/326V-III	16 x 16 x 100	6	-	-	ø25/ø25	5/4	ø26/ø32	
B0385/6 (L)-III	16 x 16 x 100/20 x 20 x 125	11/1	-	-	ø32, ø25/ø32	3-2/5	ø38	
B0385/6 (L)V-III	16 x 16 x 100/20 x 20 x 125	5/1	-	-	ø32, ø25/ø32	3-2/5	ø38	
B038T	-	-	20 x 20 x 125	St.8	ø32/ø25		ø38	
BH20/BH20Z	12 x 12 x 85	4	12 x 12 x 85	St.12	ø25/ø32		ø20	
BH38	16 x 16 x 125	5	20 x 20 x 125	St.12	ø25/ø32		ø38.1	
C150/CH154	12 x 12 x 60 ~ 100	4 ~ 6	-	-	-	-	ø80	
C180	12 x 12 x 60 ~ 100	4 ~ 6	-	-	-	-	ø120	
C220/220T	12 x 12 x 60 ~ 100	6 ~ 8	-	-	-	-	ø120	
C300-IV	16 x 16 x 100 ~ 130	6 ~ 10	-	-	-	-	ø165	
C300H	16 x 16 x 100 ~ 130	6 ~ 10	-	-	-	-	ø165	
P013	8 x 8 x 100 ~ 120	6	-	-	ø16/-	3/-	ø1	
P014	8 x 8 x 100 ~ 120	6	-	-	ø16/ø16	3/3	ø1	
P033	8 x 8 x 100 ~ 120	6	-	-	ø16/-	3/-	ø3	
P034	8 x 8 x 100 ~ 120	6	-	-	ø16/ø16	3/3	ø3	
S205/206	12 x 12 x 100	8	-	-	ø22/ø20	5/4	ø20	
S205/206-II	12 x 12 x 100	9	-	-	ø25/ø25	7/4(8)	ø20	
SS207/SS207-5AX	12 x 12 x 100	8	-	-	ø22/ø20	4/4	ø20	
SS26	16 x 16 x 100	7	-	-	ø22/ø20	5/3	ø26	
SS32/32L	16 x 16 x 100	7	-	-	ø22/ø20	5/3	ø32	
SS267/SS267-5AX	16 x 16 x 100	8	-	-	ø25/ø25	4/4	ø26	
SS327/SS327-5AX	16 x 16 x 100	8	-	-	ø25/ø25	4/4	ø32	
BW269ZJ	16 x 16 x 100	7	-	-	ø25/ø25	5/(8)	ø26	
BW329ZJ	16 x 16 x 100	7	-	-	ø25/ø25	5/(8)	ø32	
MB25	-	-	20 x 20 x 90	2 x St.8	ø20/ø32	5/4	ø25	
M06JC-II	-	-	20 x 20 x 125	St.8	ø25		ø220/ø42	
M06J-II	-	-	25 x 25 x 150	St.8	ø32/ø40		ø260/ø51	
M08J-II	-	-	25 x 25 x 150	St.8	ø32/ø40		ø280/ø65	
M08JL5-II	-	-	25 x 25 x 150	St.8	ø32/ø40		ø280/ø65	
M08JL8-II	-	-	25 x 25 x 150	St.8	ø32/ø40		ø280/ø65	
M06D-II	-	-	25 x 25 x 150	St.12	ø40		ø260/ø51	
M08D-II	-	-	25 x 25 x 150	St.12	ø40		ø280/ø65	
M06DY-II	-	-	25 x 25 x 150	St.12	ø40		ø260/ø51	
M08DY-II	-	-	25 x 25 x 150	St.12	ø40		ø280/ø65	
M06SJ-II	-	-	25 x 25 x 150	St.12	ø40		ø260/ø51	
M08SJ-II	-	-	25 x 25 x 150	St.12	ø40		ø280/ø65	
M06SD-II	-	-	25 x 25 x 150	St.12	ø40		ø260/ø51	
M08SD-II	-	-	25 x 25 x 150	St.12	ø40		ø280/ø65	
M06SY-II	-	-	25 x 25 x 150	St.12	ø40		ø260/ø51	
M08SY-II	-	-	25 x 25 x 150	St.12	ø40		ø280/ø65	
TMU1	20 x 20 x 100 ~ 125	1	20 x 20 x 125	St.16	ø32/ø32		ø38	
TMB2	20 x 20 x 100 ~ 125	1	20 x 20 x 125	St.16	ø32/ø32		ø51	
TMA8F	20 x 20 x 100 ~ 125	1	-	-	ø32/ø32		ø65	
TMA8J	20 x 20 x 100 ~ 125	1	-	-	ø32/ø32		ø65	
TMA8H	20 x 20 x 100 ~ 125	1	-	-	ø32/ø32		ø65	

Manufacturers are in no particular order.



Automatic lathe list by manufacturer

Nomura DS

Model	Toolholder dimensions (Gang tool post)	Number of tools	Toolholder dimensions (Turret tool post)	Number of tools	Sleeve dia. (Horizontal/Opposed)	Number of tools	Max. cutting dia.	Remarks
NN-10C	10 x 10 x 130	6			ø17		ø10	
NN-10CS	10 x 10 x 130	5			ø17	4	ø10	
NN-10SII	10 x 10 x 130	5			ø23		ø10	
NN-10T	10 x 10 x 130	7			ø23		ø10	
NN-10SB5	10 x 10 x 130	5			ø23		ø13	
NN-10EX2	10 x 10 x 120	6			ø16	4	ø10	
NN-10EX2	10 x 10 x 80	7			ø16	4	ø10	
NN-16SB5	10 x 10 x 130	5			ø23		ø16	
NN-16SB6 Type1	12.7 x 12.7 x 130*	7			ø17(ø22)	4	ø16	
NN-16SB6 Type2	12.7 x 12.7 x 130*	5			ø17(ø22)	4	ø16	
NN-16SB6 Type2.5	12.7 x 12.7 x 130*	6			ø17(ø22)	5	ø16	
NN-16SB6 Type3	12.7 x 12.7 x 130*	5			ø17(ø22)	4	ø16	
NN-16SB7	12.7 x 12.7 x 130*	5			ø16	4	ø16	
NN-16SB7-M8	12.7 x 12.7 x 130*	5			ø16	4	ø16	
NN-20SB	12.7 x 12.7 x 130*	5			ø16	3	ø20	
					ø22	2	ø20	
NN-16HIII	12 x 12 x 130	6			ø23		ø16	
NN-20HIII	12 x 12 x 130	6			ø23		ø20	
NN-16UIII	12 x 12 x 130	5			ø23		ø16	
NN-20UIII	12 x 12 x 130	5			ø23		ø20	
NN-20CS	12.7 x 12.7 x 130	5(6)			ø22	4	ø20(ø25)	
NN-20U5	12.7 x 12.7 x 150	5(6)			ø22	4	ø20(ø25)	
NN-32U5	12.7 x 12.7 x 150	3(4)			ø32	1		
	16 x 16 x 130	2			ø22	3	ø32	
NN-16UB5	12 x 12 x 130	5			ø23		ø16	
NN-20UB5	12 x 12 x 130	5			ø23		ø20	
NN-20UB7	12 x 12 x 130	6			ø23		ø20	
NN-20UB8	12.7 x 12.7 x 150*	5(6)			ø22	4	ø20(ø25)	
NN-20UB10	12.7 x 12.7 x 150*	5(6)			ø22	4	ø20(ø25)	
NN-32UB8	12.7 x 12.7 x 150*	3(4)			ø32	1		
	16 x 16 x 130	2			ø22	3	ø32	
NN-32UB10W	12.7 x 12.7 x 150*	3(4)			ø32	1		
	16 x 16 x 130	2			ø22	3	ø32	
NN-20YB	12 x 12 x 130	6			ø23		ø20	
NN-25YB/32YB	16 x 16 x 130	5			ø23/ø32		ø25/ø32	
NN-32YB5	16 x 16 x 130	5			ø22/ø32	4	ø32	
NN-32YB5 XB	16 x 16 x 130	6			ø22/ø32	5/1	ø32	
NN-16J	12.7 x 12.7 x 130*	6			ø23		ø16	
NN-20J	12.7 x 12.7 x 130*	6			ø23		ø20	
NN-20J2	12.7 x 12.7 x 130*	6			ø22	4	ø20	
NN-20J5	12.7 x 12.7 x 130*	6			ø22	4	ø20	
NN-20J5 XB	12.7 x 12.7 x 130*	5			ø22	4	ø20	
NN-32J	16 x 16 x 130	6			ø25	2		
					ø32	3	ø32	
NN-32DB	16 x 16 x 130	8			ø22	4		
					ø32	1	ø32	
NN-38KM	16 x 16 x 130	5			ø25	3		
					ø32	2	ø38	

* 12 x 12 toolholder mountable

Manufacturers are in no particular order.

R



Technical information

R53

Automatic lathe list by manufacturer

List of instruments and applicable small parts machining and toolholders

Models of major machine tool manufacturers				Applicable toolholders
Manufacturer	Model (Automatic lathe)	Toolholder size	Total length of attached toolholder (Max.)	
Citizen Machinery	A12,A16,B12,L12,RL01,RL21	10 x 10	100	...1010F-..
	K12,K16	12 x 12		...1212F-..
	RL02	16 x 16		...1616H-..
	B12E,B16E,BL12,C12,C16,M12,M16 MSL12	10 x 10	120	...1010JX-..
	A20,A20VII,B20,BL20,BL25,K12E,K16E L20X,L220,MC20	12 x 12		...1212JX-..
	L16,L20,L20E	12 x 12	130	...1212JX-..
	C32,L25,L32,M20,M32	16 x 16		...1616JX-..
	A32,D25		150	
Star Micronics	SW-12RII	10 x 10	120	...1010JX-..
	SB-16A,SB-16C,SB-16D,SB-12II,SB-16II SB-12R/16R/20R,SR-20IV,SB-20A/C/E,SC20	12 x 12	130	...1212JX-..
	SR-20RII,SR-20III,SV-12,SV-20,SR-20J	12 x 12	135	...1212JX-..
	SV-20R,SV-32,SV-38R,SR-38J,SX-38	16 x 16		...1616JX-..
	SR-25J,SR-32J,SW-20	16 x 16	150	...1616JX-..
Tsugami	B0,BH20,BM,BW2	12 x 12	85	...1212F-..
	C150,C180,C220,S205,S206,SS207	12 x 12	100	...1212F-..
	BH38,B0265,B0266,B0325,B0326 SS26,SS32/32L,SS267,SS327	16 x 16		...1616H-..
Nomura DS	NN-10C,NN-10CS,NN-10EX2,NN-10SII NN-10SB5,NN-10T,NN-16SB5	10 x 10	130	...1010JX-..
	NN-16HIII,NN-16UB5,NN-16UIII NN-20HIII,NN-20UIII,NN-20UB5,NN-20YB	12 x 12		...1212JX-..
	NN-25YB,NN-32YB5,NN-32J,NN-38KM	16 x 16		...1616JX-..

Manufacturers are in no particular order.

R



Technical information

R54

Parts compatibility of lever lock toolholders

Parts compatibility of lever lock toolholders

- 1) For better usability of lever lock toolholders, some levers, lock screws and shims are modified.
- 2) It is highly recommended to use only new parts. However, they are compatible with conventional parts and can be used together with them.
- 3) It is possible to use new parts only with a toolholder which has been in use.
- 4) When purchasing replacements, order them stating the new numbers.
- 5) Some of the shims remain unmodified.

Classification	Toolholder description	Spare parts							
		Lever		Lock screw		Shim			
		New No.	Conventional	New No.	Conventional	New No.	Conventional		
External turning toolholders	PCLN ^{R/L}-09	LL-1N	LL-1	LS-1N	LS-1	LC-32N	LC-32	
	-12	LL-2N	LL-2	LS-2N	LS-2	LC-42N	LC-42	
	-16	LL-5N	LL-5	LS-4N	LS-4	LC-53N	LC-53	
	PDJN ^{R/L}-11	LL-1DN	LL-1D	LS-1N	LS-1	LD-32N	LD-32	
	-15	LL-3N	LL-3	LS-2N	LS-2	LD-42		
	PSBN ^{R/L}-09	LL-1N	LL-1	LS-1N	LS-1	LS-32		
	-12	LL-2N	LL-2	LS-2N	LS-2	LS-42		
	PSKN ^{R/L}-09	LL-1N	LL-1	LS-1N	LS-1	LS-32		
	-12	LL-2N	LL-2	LS-2N	LS-2	LS-42		
	PSSN ^{R/L}-09	LL-1N	LL-1	LS-1N	LS-1	LS-32		
	-12	LL-2N	LL-2	LS-2N	LS-2	LS-42		
	PSDNN-09	LL-1N	LL-1	LS-1N	LS-1	LS-32		
	-12	LL-2N	LL-2	LS-2N	LS-2	LS-42		
Boring bars	PTGN ^{R/L}	1212F-11	LL-03N	LL-03	LS-03N	LS-03	-		
	-11	LL-03TN	LL-03T	LS-03SN	LS-03S	-		
	-16	LL-1N	LL-1	LS-1N	LS-1	LT-32N	LT-32	
	-22	LL-2N	LL-2	LS-2N	LS-2	LT-42N	LT-42	
	PTFN ^{R/L}	1212F-11	LL-03N	LL-03	LS-03N	LS-03	-		
	-11	LL-03TN	LL-03T	LS-03SN	LS-03S	-		
	-16	LL-1N	LL-1	LS-1N	LS-1	LT-32N	LT-32	
	-22	LL-2N	LL-2	LS-2N	LS-2	LT-42N	LT-42	
	PRGC ^{R/L}-12	LL-1CN	LL-1C	LS-1N	LS-1	LR-12C		
	PRXC ^{R/L}-12							
	PRGN ^{R/L}-09	LL-1N	LL-1	LS-1N	LS-1	LR-80		
	-12	LL-2N	LL-2	LS-2N	LS-2	LR-81		
	PWLN ^{R/L}-06	LL-1N	LL-1	LS-1N	LS-1	LW-32N	LW-32	
	-08	LL-2N	LL-2	LS-2N	LS-2	LW-42N	LW-42	
Turning mill	PCLN ^{R/L}	09-20	LL-03SN	LL-03S	LS-03SN	LS-03S	-		
		09-27							
		09-32	LL-1N	LL-1	LS-1SN	LS-1S	LC-32N	LC-32	
-	PCLN ^{R/L}	12-..	LL-2N	LL-2	LS-2N	LS-2	LC-42N ^{R/L}	LC-42 ^{R/L}
-	PDUN ^{R/L}	11-..	LL-1DN	LL-1D	LS-1SN	LS-1S	LD-32N	LD-32
-	PTUN ^{R/L}	11-..	LL-03TN	LL-03T	LS-03SN	LS-03S	-	
	S25R-	PTUN ^{R/L}	16-30	LL-03SN	LL-03S	LS-03SN	LS-03S	-	
	S32S-		16-40	LL-1N	LL-1	LS-1N	LS-1	LT-32N	LT-32
	S40T-		16-50						
	PWLN ^{R/L}	06-20	LL-03SN	LL-03S	LS-03SN	LS-03S	-		
		06-27							
		06-32	LL-1N	LL-1	LS-1SN	LS-1S	LW-32N	LW-32	
-	PWLN ^{R/L}	08-..	LL-2N	LL-2	LS-2N	LS-2	LW-42N ^{R/L}	LW-42 ^{R/L}
	T63H-	PCLN ^{R/L}	-DX12						
	T63H-	PCMNN	-□12	LL-2N	LL-2	LS-2N	LS-2	LC-42N	LC-42
	T63H-	PDJN ^{R/L}	-DX15						
	T63H-	PDNNN	-□15	LL-3N	LL-3	LS-2N	LS-2	LD-42	
	T63H-	PTGN ^{R/L}	-DX16	LL-1N	LL-1	LS-1N	LS-1	LT-32N	LT-32
	T63H-	PWLN ^{R/L}	-DX08	LL-2N	LL-2	LS-2N	LS-2	LW-42N	LW-42

R



Technical information

R55

